Citation for published version:

Ayers, MP, Clift, SE & Gheduzzi, S 2014, 'Morsellised sawbones is an acceptable experimental substitute for the in vitro elastic and viscoelastic mechanical characterisation of morsellised cancellous bone undergoing impaction grafting', *Medical Engineering and Physics*, vol. 36, no. 1, pp. 26-31.
<https://doi.org/10.1016/j.medengphy.2013.08.005>

DOI:

[10.1016/j.medengphy.2013.08.005](https://doi.org/10.1016/j.medengphy.2013.08.005)

Publication date:

2014

Document Version

Peer reviewed version

[Link to publication](#)

Publisher Rights

CC BY-NC-ND

University of Bath

Alternative formats

If you require this document in an alternative format, please contact:
openaccess@bath.ac.uk

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

UNIVERSITY OF
BATH

Ayers, M. P., Clift, S. E. and Gheduzzi, S. (2014) Morsellised sawbones is an acceptable experimental substitute for the in vitro elastic and viscoelastic mechanical characterisation of morsellised cancellous bone undergoing impactation grafting. Medical Engineering and Physics, 36 (1). pp. 26-31. ISSN 1350-4533

Link to official URL (if available):

<http://dx.doi.org/10.1016/j.medengphy.2013.08.005>

Opus: University of Bath Online Publication Store

<http://opus.bath.ac.uk/>

This version is made available in accordance with publisher policies.
Please cite only the published version using the reference above.

See <http://opus.bath.ac.uk/> for usage policies.

Please scroll down to view the document.

Morsellised sawbones is an acceptable experimental substitute for the in-vitro elastic and viscoelastic mechanical characterisation of morsellised cancellous bone undergoing impaction grafting.

M P Ayers, S E Clift & S Gheduzzi

Centre for Orthopaedic Biomechanics

Department of Mechanical Engineering

University of Bath, UK

Corresponding author:

Dr S E Clift email: s.e.clift@bath.ac.uk

Word count: 3902

Abstract

Impaction grafting using morsellised bone chips is widely used during surgery to mitigate the effects of bone loss. The technique typically involves the packing of morsellised allograft cancellous bone into bone defects, and has found extensive application in revision hip and knee surgery. In the ideal situation, the presence of the bone graft prevents subsidence of the revised prosthesis in the short term, and integrates with the host bone in the longer term. However, the configuration of particles within the graft remains to be optimised, and is highly likely to vary across potential sites and loading conditions. Human bone, for use in experimental investigation, is often difficult to obtain with properties that are relevant from a clinical point of view. This study, therefore, has explored the mechanical response of a Sawbones based experimental substitute. An established confined compression technique was used to characterise the morsellised Sawbones material. Comparison of the results with published values for bovine and human bone indicate that the mechanical response of the morsellised Sawbones material map well onto the elastic and viscoelastic response of bone of a biological origin.

Introduction

Knee and hip replacements are very widely performed procedures: The UK National Joint Registry (NJR) reports 80,314 hip replacements and 84,653 knee replacements for 2011 in England and Wales alone: The ratio of primary to revision procedures is reported as 6.1% for knees and 11% for hips [1]. Younger patients are more likely to need revision surgery [2]. Patients who have had a revision are more than five times more likely to need a re-revision, compared with a primary arthroplasty [3]. Worldwide the figures are expected to increase substantially over the next few years [4].

Patients frequently present for revision with a significant loss of bone stock, and this can be exacerbated during the removal of the old prosthesis [5]. Stabilisation of the revision implant may well require that bone stock is enhanced in key areas, leading to the use of techniques such as allograft bone impaction grafting. The technique was first developed in 1984 by Sloof et al [26] to improve bone stock deficiency in protusio acetabuli and, in 1991, it was adapted by the Exeter group to address femoral bone deficiency [27]. Impaction grafting essentially involves using packed chips of cancellous bone to mitigate the effects of bone loss in revision hip or knee surgery whereby the graft surrounds the revision implant granting it immediate post-operative stability. It has been demonstrated that, when appropriate conditions are met, bone stock can be restored in the long term with the graft being incorporated into the host [28]. Reported clinical outcomes are generally good, however the success rates achieved by the developers of the technique appear to be largely unmatched by other centres [29]. There is long established general agreement that success in allograft impaction grafting is strongly linked to the creation of a favourable mechanical environment, hence the surgical technique and the care with which it is adopted are paramount [30,31]. Future improvement depends upon further understanding of the mechanics of the bone construct and the factors that affect its consolidation and, eventually, remodelling and incorporation into the patient's own tissue.

(line 60)

Impaction grafting has been demonstrated to be a successful and progressively improving surgical technique at its best producing good long term bony support [6]. However, availability of human allograft bone is an issue, with demand exceeding supply [7,8]. Transmission of disease is also a significant concern [9], as is the degradation of longer term mechanical performance associated with sterilisation techniques such as irradiation [32].

Clinically, this has led to an interest in synthetic graft extenders eg hydroxyapatite [10,11] which may also change to the mechanical environment [12].

68 The level of availability of human allograft bone has had a significant impact on biomechanical
69 studies exploring impaction grafting. Bovine, porcine and ovine bone have all been investigated as
70 substitutes that can potentially be used in experimental investigations of the mechanical response of
71 morsellised cancellous bone (MCB) [13]. The challenge in mechanical characterisation of morsellised
72 bone is to devise an experimental protocol which separates out the pressure dependent elastic
73 properties from the time dependent viscoelastic and the plastic properties. Methodologies to do
74 this, based on a confined compression testing procedure originating in soil mechanics, have been
75 presented most recently by Phillips et al [14,15] and Lunde et al [16]. In this study, we have used the
76 methodology of Phillips et al [15] and postulate that a synthetic “Sawbones” morsellised bone
77 substitute (Solid Rigid PU Foam, code 30pcf) will exhibit similar mechanical behaviour to the
78 biological based alternatives. 30pcf was chosen as it readily available and falls in the mid-range of
79 the different densities of solid rigid polyurethane foam testing blocks produced by Sawbones and
80 conforming to ASTM F-1839-08 “Standard specification for Rigid Polyurethane Foam for Use as a
81 Standard Material for Testing Orthopaedic Devices and Instruments”.

82 Experimental investigations into the primary stability of impacted bone graft use variants of the
83 confined compression test to represent physiological loading constraints. Many studies have
84 focussed on the comparison of the effect of a particular parameter e.g. hydraulic and manual driven
85 impaction loading protocols (Putzer et al [33] and size of the morsellised bone particles (Board et al.,
86 [34] , Toms et al., [35] , Bolder et al., [36] , Arts et al., [37] , Brewster et al., [38] , Dunlop et al [39]).
87 Unfortunately, direct comparison of findings across different experimental studies is problematic
88 due to the lack of standardisation in (i) the test configuration (e.g. Butler et al [40] , Lunde et al
89 ([41]), Putzer et al [33], Aquarius et al [42], Bolland et al [43]; (ii) the magnitude and frequency of
90 loading (Bavadekar et al [19], Fosse et al [23], Grimm [18], Voor et al [22]; (iv) the origin and
91 treatment of the bone chips (Cornu et al [20], Datta et al [13], Lunde et al ([44])). One approach that

potentially alleviates the difficulties of comparison across studies is to use experimental protocols which enable the bone graft material to be characterised using consolidation models from soil mechanics, such as the Drucker-Prager and Mohr-Coulomb yield criteria. This then offers the possibility of employing computer based stress analysis techniques to help inform experimental and clinical observations (e.g. Phillips et al [45], Lunde & Skallerud [25], Albert et al [46])

(Materials and Method

The testing procedure used in this study was similar to that developed by Phillips et al [15] and subsequently adopted by Lunde et al [16] with minor modifications. This allows for direct comparison with the results obtained in these previous studies.

Testing arrangement:

Confined compression testing was used, where the samples were confined within a die produced from a cylindrical section of mild steel with an internal diameter of 51mm, a wall thickness of 9mm and a length of 100mm (Figure 1). The diameter of the die meant that the size of the bone graft particles would be small in comparison, minimising any interaction between the particles and the die [14,15]. The large wall thickness prevented radial strains from significantly altering the geometry of the cavity during testing. The die was secured to its base plate using three screws threaded through its wall, allowing easy removal of the samples following testing. Loading was applied to the samples through a plunger, rigidly attached to a materials testing machine (Instron, model no. 3360, High Wycombe). The plunger was a solid steel cylinder with a diameter of 50mm. The 1mm clearance allowed between die and plunger was small enough to ensure adequate constraint of the bone graft, whilst minimising interaction between both components.

Specimen preparation:

Polyurethane foam produced by Sawbones (Sawbones, product no. 1522-04, Malmö, Sweden) was used to create a dry morsellised bone substitute material. With a compressive strength of 18MPa and a compressive modulus of 445MPa, in its solid test block form, the material has mechanical properties that are within the range of human cancellous bone. A Norwich bone mill (Howmedica now Stryker, Mahwah, New Jersey USA) was used to create synthetic MCB particles. The morsellised Sawbones particles were passed through a series of sieves to ensure their distribution ranged in size between 1-6mm; visual inspection was used to remove particles larger than 6mm. This size range not only is consistent with that of clinically used particles for femoral impaction grafting [ref d] but it also reduced the risk of edge effects affecting the results. Particle size distribution was not recorded in this study.

Experimental procedure: Elastic and viscoelastic characterisation

Samples were introduced into the die in three roughly equal layers; a 20N static load was applied to each layer for approximately 5 sec in order to standardise the compression applied to each sample at the time of insertion into the die. A standardised loading profile was then applied to each sample in three stages: conditioning, re-loading and unloading. During the conditioning stage, samples were subject to 750 cycles, with each cycle loading the sample to a maximum nominal stress of 3.0MPa and unloading to an minimum nominal stress of 0.01MPa (close to zero). The load was applied at a constant displacement rate of 10mm/min. Time, plunger displacement and load applied to the samples were continually recorded. The aim of this conditioning stage was to ensure that the specimen was very well packed so that subsequent testing at physiological stress level would produce a response which could be assumed completely elastic in nature. Following the conditioning cycles, the plunger was removed from the test chamber and the sample was left to rest

for 16 hours while still inside the die. Five samples were then re-loaded to each of six stress levels (0.5, 1.0, 1.5, 2.0, 2.5 and 3.0 MPa), and were left to stress relax by for a period of 6 hours. This was achieved by maintaining the displacement of the plunger constant once the required loading level had been reached and by monitoring the fall in load versus time. Given that the geometry of the sample can be approximated to the internal geometry of the die the decreasing uniaxial compressive stress can be plotted as a function of elapsed time.

Data analysis procedure: Elastic and viscoelastic response.

Data analysis was carried out following the theoretical framework developed by Phillips et al [15] and adopted, with only some slight changes in notation, by Lunde et al [16]. This is briefly described below; wherever possible the same notation as Phillips et al [15] has been adopted.

The equilibrium constrained elastic modulus of MCB (E^∞) can be expressed as a linear function the equilibrium of hydrostatic pressure (p^∞) [15,16]:

$$E^\infty = c_1 + c_2 p^\infty \quad (1)$$

Where c_1 and c_2 are constants, E^∞ and p^∞ are the elastic modulus and hydrostatic pressure at $t = \infty$, hence once equilibrium conditions have been reached by the sample.

For uniaxial confined compression, the hydrostatic equilibrium pressure p^∞ is related to the uniaxial equilibrium stress, σ^∞ , via a Poisson's ratio, ν :

$$\sigma^\infty = p^\infty \left(\frac{1}{3} + \frac{2\nu}{3(1-\nu)} \right) \quad (2)$$

For each stress relaxation experiment the uniaxial equilibrium stress, σ_n^∞ , can be extrapolated. Phillips [17] has shown that, for MCB samples, the instantaneous uniaxial stress, $\sigma_n(t)$, can be described by a modified third order Prony series:

$$\sigma_n(t) = \sigma_n^\infty + k_n \left(e^{\frac{-t}{100}} + e^{\frac{-t}{1000}} + e^{\frac{-t}{10000}} \right) \quad (3)$$

where t is the time elapsed and k_n is a constant.

In summary, the elastic behaviour of MCB is characterised by the magnitude of the constants c_1 and c_2 ; while the viscoelastic behaviour by the parameters σ^∞ and k .

Testing procedure: Plastic characterisation

Prior to testing, samples of dry bone substitute were packed into the test chamber in 5 roughly equal layers. Following the insertion of each layer, five impactions were applied to each test sample. These impactions were designed to simulate the impaction of the bone graft during surgery and were performed through the use of an impaction rig developed by Grimm [18]. The impaction rig

181 allowed the standardization of the impactation procedure in a way that would not be possible if the
182 samples were impacted by hand. The impactation rig is shown in Figure 2 and consisted of a mass that
183 could be dropped along a guide wire and onto a plunger resting on the dry bone substitute sample.
184 The guide wire was screwed into both the bottom of the test die and the top of the impactation rig.
185 Tensioning the guide wire allowed the mass to pass smoothly over it. A drop-height was selected
186 such that values for momentum and energy of the mass were consistent with the literature [18-23].
187 Selecting a drop height of 0.28m for a 1.4kg mass produced a momentum of 3.28Ns and energy of
188 3.85J upon impact with the plunger. After each layer of dry bone substitute was added to the die,
189 the drop height was re-measured such that the momentum and energy supplied to the sample
190 remained constant.

191
192 After impacting the dry bone substitute up to a height of 100mm into the die, the guide wire was
193 removed, taking care not to disturb the compacted material. It was noticed that upon removal of the
194 guide wire, a 4mm diameter hole was left in the sample. This hole was not accounted for since the
195 influence of a similar sized hole on a comparable sample of MCB was found to be negligible [16]. The
196 sample was then subjected to 600 cyclic loading cycles applied under uniaxial compression by a
197 plunger rigidly attached to a materials testing machine (Instron, model no. 3360, High Wycombe) at
198 a constant displacement control rate of 10mm/minute. The 600 cyclic loading cycles were applied in
199 twelve sets of 50 cycles. The first 50 cycles had a maximum uniaxial compressive stress of 0.25MPa
200 and a minimum uniaxial compressive stress of 0.01MPa (near zero). The maximum uniaxial
201 compressive stress increased by a further 0.25MPa for each subsequent set of loading cycles, with
202 the twelfth set of loading cycles having a maximum uniaxial compressive stress of 3.0MPa. The
203 minimum uniaxial compressive stress remained at 0.01MPa for each set of loading cycles. After each
204 set of loading cycles, the sample of dry bone substitute was allowed to stress relax for 600 seconds.
205 A flowchart showing the testing procedure is presented in Figure 3. Throughout the testing

procedure, the force exhibited by the load cell and extension of the plunger were recorded at a frequency of 2Hz. This resulted in the number of measurements for each cycle being between 50 and 100.

Data analysis procedure: Plastic response.

Phillips et al [15] described the development of axial plastic strain as a function of the axial stress:

$$\sigma = c_3(e^{(c_4\epsilon_a^p)} - 1) \quad (4)$$

Where σ is the maximum axial stress to which the series of cycles was subject, ϵ_a^p is the plastic strain defined as the strain following the 50th load cycle at each of the 12 stress levels and c_3 and c_4 are constants.

In summary, the plastic behaviour of MCB is characterised by the magnitude of the constants c_3 and c_4 .

Results

Elastic and viscoelastic response

The stress decay versus time behaviour of the bone graft substitute material during the relaxation period for each of the 6 loading levels applied in this study is illustrated in Figure 4. Each set of experimental data was fitted with equation (3) to calculate the values of σ_n^∞ and k_n where $n=1...5$

and represents the number of repetitions of each experiment at each of the 6 load levels adopted in the study. Curve fitting was performed using Matlab R2011b 24 bit (Matworks, USA); in particular the curve fitting tool was set up to take advantage of a non-linear least squares algorithm available within this software package. For each load level, average values for σ^∞ , k , were calculated from σ_n^∞ and k_n ; these are presented in Table 1 alongside with the standard error of the mean.

In the present study a value of 0.2 for Poisson's ratio was used in equation (2) to calculate the hydrostatic equilibrium pressure, p^∞ , at each applied load level given the uniaxial equilibrium stress, σ^∞ . The relationship between E^∞ and p^∞ , equation (1), was determined using a liner regression technique that allowed the effect of uncertainties arising from experimental data to be accounted for. This was achieved by fitting the experimental data points by means of a weighted least square technique, using the reciprocal value of the uncertainty in E^∞ as the weights and assuming the uncertainty in p^∞ to be negligible [24]. This allows the determination of the two constants c_1 and c_2 of equation (1) and the associated standard error (Table 2). The values thus obtained can be compared to those obtained in similar studies [15,16], also reported in Table 2.

Plastic response

The uniaxial confined compressive stress and the uniaxial compressive plastic strain experienced by the Sawbones MCB samples were calculated. The uniaxial compressive plastic strain is defined as the uniaxial compressive plastic strain following the 50th load cycle for each of the twelve stress levels [15]. Therefore, following the completion of the twelve sets of 50 load cycles, twelve distinct values of uniaxial compressive plastic strain at twelve separate uniaxial confined compressive stress levels were obtained (Figure 5).

Each set of experimental data was fitted with equation (4) to calculate the values of c_3 and c_4 . Curve fitting was performed using the curve fitting tool using a non-linear least squares algorithm in

251 Matlab R2011b 24 bit (Matworks, USA). Average values of c_3 and c_4 were then calculated and are
252 reported in Table 3 alongside with the standard error of the mean. The values thus obtained can be
253 compared to those obtained in similar studies [15,16], also reported in Table 3.

Discussion

The present study examined the mechanical behaviour of a sawbones morsellised cancellous bone substitute and compared this with published data for human MCB [16], and bovine MCB [15,16]. The elastic and viscoelastic behaviour compared well, but differences were apparent in the quantification of the plastic response. How significant these differences are is problematic to establish due to the terms of reference of these previous studies: In particular, the study of Phillips et al [15] is of limited value in performing comparisons as only one repetition per experiment was reported, and in the work of Lunde et al [16] the graft particle size is large compared to the loading rig dimensions. Lunde et al [16] also report the early loading behaviour, after one cycle of load. The present study and that of Phillips et al [15] report longer term behaviour.

Further complicating factors in any comparison across studies include the influence of the fat content of the MCB which has been shown to significantly influence the consolidation behaviour [22,25]. The advantage of morsellised sawbones in this regard is in its standardized nature with zero intrinsic fat content, which makes it attractive when attempting to control experimental conditions.

In our study, as in those of Phillips et al [15] and Lunde et al [16], the loading mode is axial consolidation. However, clinically, the effect of torsional loading may well be important.

This was a pilot study providing an initial exploration of mechanical behaviour. There was, therefore, insufficient data to provide a meaningful statistical comparison. Now that we have completed this study, we are in a position to design a statistically relevant experimental protocol for future work. Identification of a good experimental analogue material will allow us to explore the effect of the

277 large number of variables known to influence the mechanical performance of Morsellised cancellous
278 bone eg magnitude and frequency of loading, distribution of particle sizes, graft impaction protocol
279 etc.

280 Conclusion

281 This study aimed to establish the mechanical properties of an experimental substitute for
282 morsellised cancellous bone based on Sawbones polyurethane bone chips. Comparison of the
283 mechanical behaviour in confined compression demonstrated agreement with published elastic and
284 viscoelastic properties of natural bone. However, further work is needed to match the plastic
285 response of the construct, and to characterise the behaviour under different loading modes.

286

287 Acknowledgements:

288 Thanks to Richard Weston for his technical support

289 Competing interests: None declared

290 Funding: University of Bath PhD studentship

291 Ethical approval: Not required

292 List of figures:

293

294

295 **Figure 1:** – schematic/photo of test rig

296

297 **Figure 2:** Impaction rig developed by Grimm [18]

298

299 **Figure 3:** Flowchart of testing procedure

300

301 **Figure 4:** Stress relaxation of morsellised sawbones; variation in uniaxial confined compressive stress
302 with time as a function of applied stress.

303

304 **Figure 5:** Variation in axial stress with plastic strain for morsellised sawbones under confined
305 compression.

306

307 List of Tables:

308

309 **Table 1:** Summary of the parameters characterising the viscoelastic response of morsellised
310 Sawbones.

311

312 **Table 2:** Comparison of the parameters c_1 and c_2 , characterising the elastic response of MCB,
313 obtained in this study and from other studies available in the literature. Please note that the values
314 in parenthesis obtained in this study for Sawbones MCB¹ represent the Standard Error while those
315 presented by Lunde et al [16] for human MCB² represent the Standard Deviation.

316

317 **Table 3:** Comparison of the parameters c_3 and c_4 obtained in this study and from other studies
318 available in the literature. Please note that the values in parenthesis obtained in this study for
319 Sawbones MCB¹ represent the Standard Error while those presented by Lunde et al [16] for human
320 MCB² represent the Standard Deviation.

321 References

322 [1] National Joint Registry for England Wales, 9th Annual Report 2012: www.njrcentre.org.uk

323

324 [2] Wainwright C, Theis J-C, Garneti N & Melloh M, Age at hip or knee joint replacement surgery
325 predicts likelihood of revision surgery JBJS 2010, Vol 93-B, pp1411-1415

326

327 [3] Ong KL, Lau E, Suggs J, Kurtz SM & Manley MT, Risk of subsequent revision after primary and
328 revision total joint arthroplasty, Clinical Orthopedics and Related Research, 2011, Vol 468, pp3070-
329 3076

330

331 [4] Kurtz S, Ong K, Lau E, Mowat F & Halpern M. Projections of primary and revision hip and knee
332 arthroplasty in the United States from 2005 to 2030. J Bone Joint Surg Am. 2007 Vol 89(4), pp780-5.

333

334 [5] McNamara IR, Impaction bone grafting in revision hip surgery: past, present and future. Cell
335 Tissue Bank. 2010, Vol 11(1), pp57-73.

336

337 [6] Lamberton TD, Kenny PJ, Whitehouse SL, Timperley AJ & Gie GA. Femoral impaction grafting in
338 revision total hip arthroplasty. J Arthroplasty 2011, vol 26(8), pp1154-1160

339

340 [7] Abbas G, Bali SL, Abbas N & Dalton DJ. Demand and supply of bone allograft and the role of
341 orthopaedic surgeons. Acta Orthop Belg 2007, Vol 73, pp507-511

342

343 [8] Greenwald AS, Boden SD, Goldberg VM, Khan Y, Laurencin CT & Rosier RN. Bone-graft
344 substitutes: Facts, fictions, and applications JBJS 2001, Vol 83-A, Supplement 2, Part 2, pp98-103

345

346 [9] Vaishnav VS & , Vangsness CT Jr., New Techniques in Allograft Tissue Processing
347 Clinics in Sports Medicine 2009, Volume 28, pp127-141

348

349 [10] Aulakh TS, Jayasekera N, Kuiper J-H & Richardson JB. Long-term clinical outcomes following the
350 use of synthetic hydroxyapatite and bone graft in impaction in revision hip arthroplasty. Biomaterials
351 2009, Vol 30, pp1732-1738

352

353 [11] Dinopoulos H, Dimitriou R & Giannoudis PV, Bone graft substitutes: What are the options?,
354 Surgeon 2012, Vol 10(4), pp230-9.

355

356 [12] Fujishiro T, Nishikawa T, Niikura T, Takikawa S, Nishiyama T, Mizuno K, Yoshiya S & Kurosaka M,
357 Impaction bone grafting with hydroxyapatite: increased femoral component stability in experiments
358 using Sawbones. Acta Orthop. 2005, Vol 76(4), pp550-4.

359

360 [13] Datta A, Gheduzzi S, & Miles AW. A comparison of the viscoelastic properties of bone
361 grafts. Clinical Biomechanics 2006, Vol 21, pp761-766

362

363 [14] Phillips ATM, Pankaj, Brown DT, Oram TZ, Howie CR & Usmani AS, The elastic properties of
364 morsellised cortico-cancellous bone graft are dependent on its prior loading. J Biomechanics 2006a,
365 Vol 39, pp1517-1526

366

367 [15] Phillips ATM, Pankaj P, May F, Taylor K, Howie CR & Usmani AS. Constitutive models for
368 impacted morsellised cortico-cancellous bone. Biomaterials 2006b, Vol 27, pp2162-2170

369

370 [16] Lunde KB, Foss OA, Fosse I & Skallerud B. Constitutive models for constrained
371 compression of unimpacted and impacted human morselized bone grafts. Journal of
372 Biomechanical Engineering 2008, Vol 130, pp 061014-1 to 061014-8

373

374 [17] Phillips ATM. Numerical Modelling of the Pelvis and Acetabular Construct Following
375 Hip Arthroplasty. PhD thesis, The University of Edinburgh, 2005.

376

377 [18] Grimm B. Mechanical Properties of Morsellised Bone Graft and Synthetic Graft Extenders
378 for Impaction Grafting. PhD thesis, University of Bath, 2003.

379

380 [19] Bavadekar A, Cornu O, Godts B, Delloye C, van Tomme J & Banse X. Stiffness and compactness
381 of morselized grafts during impaction. Acta Orthopaedica Scandinavica 2001, Vol 72(5), pp470-476

382

383 [20] Cornu O, Schubert T, Libourton X, Manil O, Godts B, Van Tomme J, Banse X & Delloye C. Particle
384 size influence in an impaction bone grafting model. Comparison of fresh-frozen and freeze-dried
385 allografts. J Biomechanics 2009, Vol 42, pp2238-2242

386

387 [21] Voor MJ, White JE, Grieshaber JE, Malkini AL & Ullrich CR. Impacted
388 morselized cancellous bone: Mechanical effects of defatting and argumentation with hydroxyapatite
389 particles. Journal of Biomechanics 2004, Vol 37, pp1233-1239

390

391 [22] Voor MJ, Nawab A, Malkini AL & Ullrich CR. Mechanical properties of
392 compacted morselized cancellous bone graft using one-dimensional consolidation testing.
393 Journal of Biomechanics 2000, Vol 33, pp1683-1688

394

395 [23] Fosse L, Rønningen H, Lund-Larson J, Benum P & Grande L. Impacted bone stiffness measured
396 during construction of morsellised bone samples. Journal of Biomechanics 2004, Vol 37, pp1757-
397 1766

398

399 [24] Taylor JR. An Introduction to Error Analysis. University Science Books, United States of America,
400 2nd edition, 1997.

401

402 [25] Lunde KB & Skallerud B. The modified cam clay model for constrained compression of human
 403 morsellised bone: Effects of porosity on the mechanical behaviour. Journal of the Mechanical
 404 Behaviour of Biomedical Materials 2009, Vol 2, pp43-50

405 [26] Slooff TJ, Huiskes R, van Horn J and Lemmens AJ. Bone grafting in total hip replacement for
 406 acetabular protusion. Acta Orthop Scand 1984;186:29-37

407 [27] Gie GA, Linder L, Ling RS, Simon JP, Slooff TJ, and Timperley AJ. Impacted cancellous allografts
 408 and cement for revision total hip arthroplasty JBJS [Br] 1993;75:14-21

409 [28] Nelissen RG, Bauer TW, Weidenhielm LR, Legolvan DP and Mikhail WE. Revision hip arthroplasty
 410 with the use of cement and impaction grafting. Histological analysis of four cases. JBJS [Am]
 411 1995;77:412-22

412 [29] Toms AD, Barker RL et al Impaction bone grafting in revision joint replacement surgery. JBJS
 413 [Am] 2004;86:2050-2060

414 [30]

415 Slooff TJ, Schimmel JW, Buma P.

416 Cemented fixation with bone grafts.

417 Orthop Clin North Am. 1993 Oct;24(4):667-77.

418

419 [31] Knight JL, Helming C. Collarless polished tapered impaction grafting of the femur during revision
 420 total hip arthroplasty: pitfalls of the surgical technique and follow-up in 31 cases. J Arthroplasty. 2000
 421 Feb;15(2):159-65.

422 [32] Costain DJ, Crawford RW. Fresh-frozen vs. irradiated allograft bone in orthopaedic
 423 reconstructive surgery. Injury. 2009 Dec;40(12):1260-4. doi: 10.1016/j.injury.2009.01.116.

424 [33] Putzer D, Mayr E, Haid C, Reinthaler A, Nogler M.

425 Impaction bone grafting: a laboratory comparison of two methods.
 426 J Bone Joint Surg Br. 2011 Aug;93(8):1049-53. doi: 10.1302/0301-620X.93B8.26819.
 427

428 [34] Board TN, Rooney P, Kearney JN, Kay PR.
 429 Impaction allografting in revision total hip replacement.
 430 J Bone Joint Surg Br. 2006 Jul;88(7):852-7
 431

432 [35] Toms AD, Barker RL, Jones RS, Kuiper JH.
 433 Impaction bone-grafting in revision joint replacement surgery.
 434 J Bone Joint Surg Am. 2004 Sep;86-A(9):2050-60
 435

436 [36] Bolder SB, Verdonschot N, Schreurs BW. Technical factors affecting cup stability in bone
 437 impaction grafting. Proc Inst Mech Eng H. 2007 Jan;221(1):81-6.

438 [37] Arts JJ, Verdonschot N, Buma P, Schreurs BW. Larger bone graft size and washing of bone grafts
 439 prior to impaction enhances the initial stability of cemented cups: experiments using a synthetic
 440 acetabular model. Acta Orthop. 2006 Apr;77(2):227-33.

441 [38] Brewster NT, Gillespie WJ, Howie CR, Madabhushi SP, Usmani AS, Fairbairn DR.
 442 Mechanical considerations in impaction bone grafting.
 443 J Bone Joint Surg Br. 1999 Jan;81(1):118-24.
 444

445 [39] Dunlop DG, Brewster NT, Madabhushi SP, Usmani AS, Pankaj P, Howie CR Techniques to
 446 improve the shear strength of impacted bone graft: the effect of particle size and washing of the
 447 graft. J Bone Joint Surg Am. 2003 Apr;85-A(4):639-46.

448 [40] Butler AM, Morgan DA, Verheul R, Walsh WR.
 449 Mechanical properties of gamma irradiated morselized bone during compaction.
 450 Biomaterials. 2005 Oct;26(30):6009-13
 451

452 [41] Lunde KB, Kaehler N, Rønningen H, Fosse L. Pressure during compaction of morsellised bone
 453 gives an increase in stiffness: an in vitro study.
 454 J Biomech. 2008;41(1):231-4.
 455

456 [42] Aquarius R, Walschot L, Buma P, Schreurs BW, Verdonschot N.
 457 In vitro testing of femoral impaction grafting with porous titanium particles: a pilot study.
 458 Clin Orthop Relat Res. 2009 Jun;467(6):1538-45. doi: 10.1007/s11999-008-0688-3
 459

460 [43] Bolland BJ, New AM, Madabhushi SP, Oreffo RO, Dunlop DG.
 461 Vibration-assisted bone-graft compaction in impaction bone grafting of the femur.
 462 J Bone Joint Surg Br. 2007
 463

464 [44] Lunde KB, Foss OA, Skallerud B. On the applicability of bovine morsellized cortico-cancellous
 465 bone as a substitute for human morsellized cortico-cancellous bone for in vitro mechanical testing. J
 466 Biomech. 2008 Dec 5;41(16):3469-74. doi: 10.1016/j.jbiomech.2008.08.030.
 467

468 [45] Phillips AT, Pankaj P, Howie CR, Usmani AS, Simpson AH.
 469 3D non-linear analysis of the acetabular construct following impaction grafting.
 470 Comput Methods Biomech Biomed Engin. 2006 Jun;9(3):125-33.
 471

472 [46] Albert C, Masri B, Duncan C, Oxland T, Fernlund G.
473 Impaction allografting--the effect of impaction force and alternative compaction methods on the
474 mechanical characteristics of the graft.
475 J Biomed Mater Res B Appl Biomater. 2008 Nov;87(2):395-405. doi: 10.1002/jbm.b.31117.
476

477

478

479

480

481

482 Figure 1

483

484

485 Figure 2

Figure 3

492

493

494 **Figure 4**

495

Figure 5

500

501

	First period of stress relaxation					
σ^0	0.5	1.0	1.5	2.0	2.5	3.0
σ^∞	0.3413±0.0065 <i>0.2937</i>	0.6931±0.0117 <i>0.6296</i>	1.0778±0.0060 <i>0.9430</i>	1.4482±0.0129 <i>1.388</i>	1.7626±0.0083 <i>1.605</i>	1.9648±0.0264 <i>1.969</i>
k	0.05846±0.00463 <i>0.04109</i>	0.10575±0.00622 <i>0.06900</i>	0.14496±0.00716 <i>0.1122</i>	0.19028±0.00367 <i>0.1515</i>	0.22250±0.00517 <i>0.2185</i>	0.34126±0.01434 <i>0.2904</i>

502 **Table 1**

503

Material	c_1 (N/mm ²)	c_2
Sawbones ¹	6.76(0.45)	14.6(0.58)
Bovine (Phillips et al [15])	3.00	26.64
Human - finger packing (Lunde et al [16]) ²	3.90(0.29)	13.00(0.32)
Human – one layer impaction (Lunde et al [16]) ²	4.10(0.60)	15.20(0.43)
Human – two layer impaction (Lunde et al [16]) ²	5.10(0.10)	13.00(1.16)

504

505 **Table 2**

Material	c_3 (N/mm ²)	c_4
Sawbones ¹	1.300(0.156)	5.3(0.3)
Bovine (Phillips et al [15])	0.5464	4.9120
Human - finger packing (Lunde et al [16]) ²	0.076(0.018)	10(0.4)
Human – one layer impaction (Lunde et al [16]) ²	0.041(0.008)	18(1.6)
Human – two layer impaction (Lunde et al [16]) ²	0.073(0.015)	17(0.9)

506 **Table 3**