Citation for published version:

Belardi, W & Knight, JC 2014, Negative curvature fibers with reduced leakage loss. in *Optical Fiber Communication Conference, OSA Technical Digest*. IEEE, 2014 Optical Fiber Communications Conference and Exhibition, OFC 2014, San Francisco, USA United States, 9/03/14. <https://doi.org/10.1364/OFC.2014.Th2A.45>

DOI:

[10.1364/OFC.2014.Th2A.45](https://doi.org/10.1364/OFC.2014.Th2A.45)

Publication date:

2014

Document Version

Early version, also known as pre-print

[Link to publication](#)

This paper was published in Optical Fiber Communication Conference and is made available as an electronic reprint with the permission of OSA. The paper can be found at the following URL on the OSA website: <http://dx.doi.org/10.1364/OFC.2014.Th2A.45>. Systematic or multiple reproduction or distribution to multiple locations via electronic or other means is prohibited and is subject to penalties under law.

University of Bath

Alternative formats

If you require this document in an alternative format, please contact:
openaccess@bath.ac.uk

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Negative curvature fibers with reduced leakage loss

Walter Belardi and Jonathan C. Knight

*Centre for Photonics and Photonic Materials, Department of Physics,
University of Bath, Claverton Down, Bath, BA2 7AY, UK*
w.belardi@bath.ac.uk

Abstract: We describe improved designs for “negative curvature” hollow core anti-resonant fibers. Numerical simulations show that introducing additional silica rings into the cladding results in a major reduction in the fiber leakage losses, for realizable fiber structures.

OCIS codes: (060.2280) Fiber design and fabrication; (060.2400) Fiber properties; (060.4005) Microstructured fibers.

1. Introduction

Hollow core anti-resonant fibers with a “negative curvature” of the core boundary have been developed in recent years as a route for achieving reduced fiber losses, low mode-glass overlap and wide transmission spectra [1,2]. Negative curvature fibers (NCFs) with losses as low as 24dB/km at 2.4 μ m have been demonstrated [3] and the benefits of the negative curvature have been modeled numerically [4]. These fibers could be used to handle high optical powers [5], to access new wavelengths regimes [6, 7] and for studying light/gas interactions [8]. Reduction of attenuation in this type of fiber is a challenging problem that could benefit all of these applications.

The core wall of an NCF is a high refractive index (glass) region surrounding and defining the hollow core, whose thickness satisfies an anti-resonant condition [9]. We will show that modification of the region immediately outside the core wall has a major impact on the rate of leakage from the fiber core, while leaving the anti-resonant condition of the core wall unaffected. The modifications we propose to previously-reported designs are restricted to outside of the core wall, enabling us to make direct comparison with the existing proven designs.

In this work we first describe the idea from a theoretical point of view. Then we propose a realistic design for a practical fiber and use numerical simulations to evaluate the impact of this novel structure on the fiber performance.

2. Theoretical case

The design “A” depicted in Fig. 1 shows a fiber structure that has been thoroughly studied theoretically and experimentally in [3], [10] and [5]. The radius of the fiber’s hollow core R_c is 47 μ m, the thickness of the silica core boundary t is 2.66 μ m and the inner radius of the silica cladding tube R_T is 128.75 μ m. The spectral range of interest for these parameters is between 2.8 and 3.8 μ m, between the first and second core wall resonances. We choose this fiber as the starting point of our discussion because it gives us the possibility to relate our results directly to previous work which has been experimentally validated.

In structure “B” of Fig. 1 the same fiber core radius R_c and core boundary thickness t of structure “A” have been used but the cladding holes are circles of diameter $d=58.27\mu$ m rather than “ice-cream cone” holes. The adoption of circular cladding holes removes the Fano resonances in the fiber transmission spectra [11]. As in [3], we used Comsol to perform all our numerical simulations. The calculated transmission spectra for structures “A” and “B” at wavelengths between 2.75 μ m and 4 μ m are shown in Figure 1 (purple line with dots and green full line respectively).

The field associated with the core mode is not completely confined within the hollow core, but extends beyond the silica core boundary into the cladding holes.. However if we modify the structure “B” by adding an additional ring of glass (structure “C” in Fig. 1) within the cladding holes of the fiber, we can exclude light from this area giving an improved confinement to the fiber core. We choose the outer diameter d_l of this new ring to be half of the outer diameter of the cladding holes d , and give it the same wall thickness. The transmission spectrum for this ideal design is also shown in Fig. 1 (dashed blue line). The leakage losses of the fiber have been dramatically reduced by the additional structures, by up to 3 orders of magnitude to well below 0.1dB/km, on the short wavelength side of the transmission window.

3. Practical case

The considered fiber structure “C” is not realizable because the internal silica ring is suspended in air. We now support this internal structure and thus design a similar fiber which is practical. The structure we have studied is shown in Fig. 1 (structure “D”). As we can see from the transmission spectrum in Fig. 1 (red dashed-dotted line) this practical structure should provide a reduction of leakage losses of 100 times compared to previously-reported designs (structure “B”), on the short-wavelength side of the transmission window to below 0.1dB/km.

Fig. 1: (a) Calculated leakage losses for the different structures depicted above: A (purple line with dots), B (green full line), C (blue dashed line), D (red dashed-dotted line), E (black dotted line). The insertion of additional silica rings within the cladding structure of the NCF can substantially reduce the fiber leakage losses ; (b) Calculated fraction of power in glass for all the different structures A,B,C,D,E. The additional silica rings within the cladding structure leaves the overlap between the optical mode and the silica almost unaltered.

In principle, further reduction in the leakage losses can be achieved by adding extra rings within the fiber cladding. As an example, the structure “E” of Fig. 1 has three nested rings (the diameter d_2 of the most internal circle is equal to $d/2$, the thickness of the silica layer is the same of that of all other layers t). As we can see in Fig. 1(a) (black dotted line) the addition of a third nested ring would reduce the confinement by 5 times as compared to the previous fiber structure (“D”).

4. Percentage of optical power in glass

The overlap of the core mode with the silica structure is a critical parameter, determining the NCFs performance in mid-infrared applications (where silica material absorption is a limitation) [4, 6] as well as its nonlinearity and power handling characteristics. It may also be relevant for the ultimate achievable fiber attenuation. Therefore we have studied the overlap of the optical power with the silica glass for the various fiber structures described above. The results are shown in Fig. 1(b). As we can see, despite adding additional silica to the structure, the minimum overlap of the guided mode with the glass remains almost exactly the same at around 6×10^{-5} .

5. Design tolerances

We have performed a numerical analysis of structure “D” of Fig. 1 by changing first the inner hole diameter d_1 and then the inner hole thickness t_1 (keeping all other parameters unchanged) in order to evaluate the design tolerances of this structure. The calculation of the leakage losses is made at the specific wavelength of $3.05 \mu\text{m}$. The results are shown in Fig. 2.

Fig. 2. (a) The calculated leakage losses for the structure depicted in the inset are almost identical for variations of d_1/d between 0.5 and 0.6; (b) The variation of the inner ring thickness has little effect on the fiber leakage losses for values of t_1/t between 0.8 and 1, between 0.2 and 0.4 and around 1.5.

The tolerances of this design are quite large. In Fig. 2(a) we can clearly see that the leakage losses have minor changes for values of d_1/d between 0.5 and 0.6. In Fig. 2(b) we can observe minor variations of the fiber performances for change of t_1/t between 0.8 and 1 as well as between 0.2 and 0.4 or around 1.5. The large tolerances allowed confirm that our design should be amenable to fabrication.

6. Conclusions

We have presented a novel and practical design improvement for hollow core anti-resonant fibers based on the use of additional silica rings in the cladding. We have investigated the potential benefit of this fiber structure in terms of leakage losses.

This work was funded by the UK Engineering and Physical Sciences Research Council under EP/I011315/1.

7. References

- [1] Y. Y. Wang, et al., "Low loss broadband transmission in hypocycloid-core Kagome hollow-core photonic crystal fiber," *Opt. Lett.* 36, 669–671 (2011)
- [2] A. D. Pryamikov, et al., "Demonstration of a waveguide regime for a silica hollow-core microstructured optical fiber with a negative curvature of the core boundary in the spectral region $> 3.5 \mu\text{m}$," *Opt. Express* 19, 1441–1448 (2011)
- [3] F. Yu, et al., "Spectral attenuation limits of silica hollow core negative curvature fiber," *Opt. Express* 21, 21466–21471 (2013)
- [4] W. Belardi, et al., "Effect of core boundary curvature on the confinement losses of hollow antiresonant fibers," *Opt. Express* 21, 21912–21917 (2013)
- [5] A. Ulrich, et al., "Flexible delivery of Er:YAG radiation at $2.94 \mu\text{m}$ with negative curvature silica glass fibers: a new solution for minimally invasive surgical procedures," *Biomed. Opt. Express* 4, 193–205 (2013)
- [6] A. F. Kosolapov, et al., "Demonstration of CO₂-laser power delivery through chalcogenide-glass fiber with negative-curvature hollow core," *Opt. Express* 19, 25723–25728 (2011)
- [7] J. Anthony, et al., "THz propagation in kagome hollow-core microstructured fibers," *Opt. Express* 19, 18470–18478 (2011)
- [8] F. Benabid, et al., "Light and gas confinement in hollow-core photonic crystal fibre based photonic microcells," *J. European Opt. Soc.* 4, 09004 (2009)
- [9] M. A. Duguay, et al., "Antiresonant reflecting optical waveguides in SiO₂/Si multilayer structures," *Appl. Phys. Lett.* 49, 13–15 (1986)
- [10] F. Yu, et al., "Low loss silica hollow core fibers for $3\text{--}4 \mu\text{m}$ spectral region," *Opt. Express* 20, 11153–11158 (2012)
- [11] L. Vincetti, et al., "Extra loss due to Fano resonances in inhibited coupling fibers based on a lattice of tubes," *Opt. Express* 20, 14350–14361 (2012)