Citation for published version:

Wagner, JL, Ting, VP & Chuck, CJ 2014, 'Catalytic cracking of sterol-rich yeast lipid', *Fuel*, vol. 130, pp. 315-323. <https://doi.org/10.1016/j.fuel.2014.04.048>

DOI:

[10.1016/j.fuel.2014.04.048](https://doi.org/10.1016/j.fuel.2014.04.048)

Publication date:

2014

Document Version

Peer reviewed version

[Link to publication](#)

Publisher Rights

CC BY-NC-ND

University of Bath

Alternative formats

If you require this document in an alternative format, please contact:
openaccess@bath.ac.uk

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Catalytic cracking of sterol-rich yeast lipid

Jonathan L. Wagner,^a Valeska P. Ting^b and Christopher J. Chuck^{a*}

^a Centre for Sustainable Chemical Technologies, Department of Chemical Engineering, University of Bath, Bath, UK, BA2 7AY.

^b Department of Chemical Engineering, University of Bath, Bath, UK, BA2 7AY.

*email C.Chuck@bath.ac.uk, tel: +44 (0)1225 383537, fax: +44 (0)1225 386231

1. Introduction

The mitigation of climate change by reducing global carbon emissions, whilst meeting an ever-increasing energy demand, is one of the biggest challenges of the 21st century. Emission reductions are particularly hard to achieve within the transportation sector, which accounts for 26% of total global energy consumption,¹ mainly due to its heavy reliance on energy-dense liquid fuels. Biofuels are widely seen as an important contributor to help reduce short- to medium-term emissions until non-carbon based technologies can be widely introduced. However, for biofuels to have a positive impact on global energy markets the key technological challenges that need to be addressed are associated with improving the quality of the fuel produced and ensuring the sustainability of its production.

One of the major sources of biofuels are glyceride lipids, which can be transesterified into biodiesel, comprised of fatty acid methyl esters. While biodiesel is fully miscible with diesel, fatty acid methyl esters have high cloud points, low energy densities and low oxidative stability, which have restricted their maximum blend levels to 7 % (v/v) with ULSD in the EU.^{3, 4} Increasing the future use of bio-derived fuels therefore necessitates the development of higher-quality biofuels with more compatible properties to ULSD. ULSD is a complex mixture of straight-chain and branched alkanes, cycloalkanes and aromatics. Generally, high levels of long chain alkanes in ULSD will result in higher cetane numbers and higher energy

1 density, while the presence of branched components improves the low temperature behaviour. In addition,
2 ULSD typically contains up to 20 wt% of aromatic compounds, which provide vital lubrication for the fuel
3 injection system.

4 In an attempt to improve the performance of bio-derived fuels, new processes for producing
5 biofuels with similar hydrocarbon compositions to ULSD are being developed and tend to fall within one of
6 two separate approaches.⁵ The first approach uses hydrotreating, which involves the deoxygenation of
7 triglycerides into linear chain alkanes, over Pd, Pt, Ni, Ru, Os, Rh or Ir catalysts supported on a range of
8 zeolites, aluminosilicates or activated carbons.^{6,7} This process is followed by additional isomerisation and
9 cracking reactions over Pt or Pd catalysts on zeolite supports, which improve the low temperature
10 properties of the resulting hydroprocessed ester and fatty acid ("HEFA") fuels.⁸ A number of commercial
11 hydrotreating processes for producing HEFA fuels have been licenced by companies such as Neste Oil
12 (NExBTL), Syntroleum (Bio-SynfiningTM) and Honeywell UOP/Eni (EcofiningTM) with the first renewable fuel
13 plants having come into operation over the last few years.⁹⁻¹¹ However, as well as consuming significant
14 amounts of hydrogen this method has the drawback of producing fuels with insufficient aromatic content;
15 and must be blended with diesel prior to use to achieve the required lubrication and performance.

16 The second approach that is capable of converting lipids into suitable fuels with incorporated
17 aromatic components (and the approach that is examined in this work) is catalytic cracking. Catalytic
18 cracking has gained significant interest over the last thirty years after Mobil's development of the ZSM-5
19 zeolite catalyst. This catalyst was shown to convert a wide range of feedstocks (such as methanol, latex and
20 corn oil) into a uniform product mix with high aromatic content and good selectivity towards a gasoline-
21 type fuel in a single step.^{12,13} Together with ZSM-5, Beta and Y zeolites are the most widely tested zeolites,
22 but have been unable to match the high gasoline yields and low coking performance of the former.¹⁴⁻¹⁶
23 More recently, attempts have been made to modify the catalyst structure by coating or mixing zeolite
24 catalyst with mesoporous silica, and have helped to increase aromatics selectivities and reduce coke
25 deposition on the catalysts.^{17,18} As catalytic cracking is usually carried out at atmospheric pressures of inert

1 gas (rather than requiring an external source of H₂, as is the case for hydrotreating) it could potentially
2 result in a comparatively less expensive and more sustainable process for biofuel production. However, this
3 also poses a major challenge, as the lack of hydrogen has been linked to extensive catalyst coking due to
4 the formation of 'allyl-carbenium' ions from the glycerol backbone.¹⁹ Side product formation of
5 hydrocarbon gases, LPGs and solid char is another issue, resulting in low liquid yields of around 40 – 50%.^{14,}
6 ²⁰⁻²³

7 By far the greatest determinant of the sustainability of a biofuel is the sustainability of the
8 feedstock,²⁴ which has prompted research into alternative sources such as from oleaginous microbes. Many
9 microalgal, fungal and yeast species are classed as oleaginous yet only phototrophic microalgae have been
10 significantly investigated as a biofuel feedstock to date.²⁵ Microalgae show great potential as a fuel source
11 because of high theoretical lipid yields, but harnessing the CO₂ needed for growth, expensive extraction
12 steps and low growth rates are limiting commercial development. In contrast, oleaginous heterotrophic
13 species, can grow in dense colonies and can produce yields of 100 g L⁻¹ over a week in optimized aerobic
14 conditions.²⁶ While traditionally yeasts are grown on sugars sourced from first generation crops, recent
15 scientific breakthroughs have seen more diverse cellulosic sources (and potentially waste cellulosic
16 materials) being utilised,^{27, 28} with certain species producing lipids totalling over 60% of the dry weight
17 under suitable conditions.²⁹ However, a major challenge in converting microbial lipids is in the complexity
18 of the oils, which can include compounds such as phospholipids, carotenoids and most notably a wide
19 variety of sterols including ergosterol, sitosterol and cholesterol.³⁰ While sterols are present to up to 5 wt%
20 in algal lipids they can total up to 50 wt% in some yeast oils,³¹⁻³⁴ which can pose problems for processing of
21 these feedstocks via conventional transesterification or hydrotreating routes. For transesterification
22 reactions, the high sterol content would reduce the yield and potentially saponify the catalyst, further
23 increasing the cost of the process. In the hydrotreatment of lipids, contaminants such as alkali metals,
24 phosphorous compounds and the waxes, sterols, tocopherols and carotenoids contained in natural oils and
25 fats can inhibit catalyst performance and may therefore need to be removed prior to processing.⁹⁻¹¹

Despite these concerns, to the knowledge of the authors, no research to date has been published on the effect of converting a sterol-rich microbial lipid into useable hydrocarbon fuels. Here, we investigated the effect of sterol content on the catalytic cracking of rapeseed oil over HY, HZSM-5 and Pd/C catalysts. To determine whether catalytic cracking could be used to provide a hydrocarbon fuel from a sterol-rich lipid feedstock, an unrefined yeast oil derived from the oleaginous yeast *Metschnikowia pulcherrima* was also subjected to catalytic cracking and the fuel properties of the resulting liquid product were assessed. The oil from *M. pulcherrima* was selected for this study as the yeast has been previously shown to grow on waste products and under inexpensive non-sterile conditions.³⁵ This yeast therefore offers a potential economic and sustainable source of lipid.

2. Experimental Section

2.1 Materials

General lab solvents were purchased from Sigma-Aldrich and used without further purification. Deuterated chloroform (CDCl_3) for ^1H NMR analysis was purchased from Fluorochem. Winter-grade ultra-low sulphur diesel (ULSD-1) with 0 % biodiesel was supplied by the Ford Motor Company. Rapeseed oil was purchased from a local supermarket (Co-operative group vegetable oil made from EU rapeseed) and contained 62 % mono-unsaturates, 30 % polyunsaturates and 8 % saturated esters. Cholesterol (94 %) was purchased from Sigma-Aldrich, UK. Yeast oil was extracted from *M. pulcherrima* according to literature methods.³⁶ All reagents were de-aerated and dried under standard Schlenk procedures before use. Three industrially relevant catalysts were selected for testing. Palladium on activated charcoal, (5 % Pd basis) was purchased from Sigma-Aldrich, UK and used without further purification. Y zeolite was purchased as ammonium Y zeolite from Sigma-Aldrich with a SiO_2 to Al_2O_3 ratio of 5.02, and calcined at 550 °C for 3 hr to generate the H^+ form, according to a procedure specified elsewhere.³⁷ Pelleted H^+ -ion exchanged ZSM-5 zeolite (SiO_2 to Al_2O_3 ratio of 38) was purchased from ACS Material, US, crushed, sieved and vacuum oven-dried at 80 °C

1 overnight. All catalysts were dried prior to use using standard Schlenk procedures. The crushed HZSM-5
2 and ammonium Y zeolite were both analysed by TGA prior to drying and calcination.

4 2.2 Methods

5 Conversion reactions were carried out in 50 mL batch reactors (Swagelok sample cylinder 304-L-HDF4-50,
6 sealed with ¼" NPT plugs, SS-4-P, and a high temperature Sealant, MS-TL-SGT). The reactors were loaded
7 under argon with 3 g of reactant and 0.5 g of catalyst. Heating was provided by a tubular pyrotherm
8 furnace with a Eurotherm temperature controller. Reaction temperatures ranged from 300 °C to 400 °C,
9 with a reaction time of 1 or 4 hr, measured from the time the reactor was placed inside the pre-heated
10 furnace. The temperature equilibrium for this set up is rapid, with no more than 5 minutes being needed to
11 bring the reactor to temperature. No pressure monitoring could be performed on the reactors, leading to a
12 potential reaction pressure range from a minimum of 2.0 bar in the absence of any reaction at 300 °C, to a
13 maximum of 40.5 bar at 400 °C for the reaction with the highest gas yield. Following the reaction, the
14 reactors were immediately removed from the furnace and left to cool to room temperature. The
15 chloroform/product solution was filtered prior to chloroform removal by evaporation under vacuum. The
16 filter paper with the solid products was dried in an oven overnight.

17 NMR spectroscopic measurements were carried out at 298 K using a Bruker AV500 spectrometer,
18 operating at 500.13 MHz for ¹H. GC-MS analysis was carried out using an Agilent 7890A

19 Gas Chromatograph equipped with a capillary column (60 m × 0.250 mm internal diameter) coated with
20 DB-23 ([50%-cyanopropyl]-methylpolysiloxane) stationary phase (0.25 µm film thickness) and a He mobile
21 phase (flow rate: 1.2 mL min⁻¹) coupled with an Agilent 5975C inert MSD with Triple Axis Detector. A
22 portion of the biodiesel samples (approximately 50 mg) was initially dissolved in 10 mL dioxane and 1 µL of
23 this solution was loaded onto the column, pre-heated to 150°C. This temperature was held for 5 minutes
24 and then heated to 250°C at a rate of 4°C min⁻¹ and then held for 2 minutes. The peak area was normalised
25 using the biphenyl internal standard peak area. Each sample was prepared from approximately 100 mg of

product dissolved in 10 mL of dioxane and filtered as necessary. The samples were loaded at 50 °C, and this temperature held for 3 min before heating to 270 °C at 20 °C min⁻¹. Dependent on the sample this temperature was held for between 6 and 20 min. The % areas, used as a semi quantitative method of analysis were calculated from the GC-FID chromatograph. Elemental analysis was carried out by Medac Ltd. The thermogravimetric analysis (TGA) was undertaken on a Setaram TG92 thermogravimetric analyser on ~18 mg samples of yeast solids produced from reaction at 350°C and 400°C. Samples were heated at a rate of 5 °C min⁻¹ in air.

3. Results and Discussion

3.1 Conversion of model oils

To examine the effect of the sterol content on the product distribution, three model biodiesel feedstocks (pure rapeseed oil ("RSO"), pure cholesterol, and a 50:50 mixture of the two ("RC50")) were investigated. The catalytic cracking of the three feedstocks was undertaken at temperatures of 300 °C, 350 °C and 400 °C in the presence of a catalyst (either 5 wt% Pd/C, HY Zeolite or HZSM-5 zeolite). 50 mL stainless steel reactors were loaded under argon with 3 g of the chosen feedstock and 0.5 g of catalyst. The reaction time was fixed at 1 hour, as a result of preliminary work demonstrating that 30 minutes was insufficient at lower temperatures and 4 hour reactions yielded very similar product distributions, in accordance with previous studies.^{12, 15, 16} The conversions at 300°C were shown to proceed sluggishly, even after an extended reaction period of 4 hours, supporting the use of higher conversion temperatures in industry, which can be in excess of 500 °C. Thus, only the higher temperatures (350°C and 400°C) were used in the following experimental runs.

3.2 Mass balances for model compounds

The proportions of the liquid, solid and gaseous product yields (by mass) from cracking reactions on the three model feedstocks at reaction temperatures of 350 °C and 400 °C are shown in Figure 1. For the

1 production of liquid fuels, the amount of solid and gas produced from the reaction should be minimised,
 2 although the deoxygenation of triglycerides will necessarily produce gaseous carbon oxide side products.
 3 The solid fraction consists of coke, which is the result of the conversion of the triglyceride backbone in pure
 4 vegetable oil,¹⁹ and is an undesirable byproduct that causes fouling and poisons the catalyst surface.

5 The solid fraction of the reaction products was calculated from the weight of the solid residue,
 6 minus the initial catalyst weight, following drying in a low-temperature oven overnight. The liquid fraction
 7 (defined as the product fraction soluble in chloroform) was recorded as the weight of

Fig. 1 Proportions of liquid (white fraction), solid (black fraction) and gas-phase (striped fraction) products from conversion of rapeseed oil (RSO), RC50 and cholesterol (CHL) at 350 °C and 400 °C, with no catalyst and in the presence of H-ZSM5, HY and Pd/C catalysts.

the liquid product once the chloroform had been removed via evaporation. The gas fraction (consisting of primarily CO₂, CO and possibly water and short chain alkanes) was calculated from the difference between the weight of the initial feedstock and the combined weight of solid and liquid products. Error bars were plotted based on the standard deviations obtained from three repeat runs for the conversion of RSO over HY Zeolite at 400 °C and Pd/C at 350 °C and the conversion of RC50 over Pd/C at 400 °C.

In all of the cracking reactions tested here the major product was the liquid fraction (above 75% for RSO at 350 °C for all three catalysts). Whilst liquid yields are even higher for the non-catalytic reaction, it must be considered that the successful deoxygenation of the feedstock will necessarily produce gaseous carbon oxides and therefore limit the maximum possible liquid yields. Raising the reaction temperature from 350 °C to 400 °C resulted in an increase in the gaseous component and a drop in liquid product yields of between 10 and 20 wt% over all of the catalysts tested. This is consistent with reports of deoxygenation of triglycerides in hydrocracking reactions used in industry over Pd, Pt or Ni catalysts, where higher temperatures led to increased cracking activity, increasing the production of gaseous products and consequently reducing liquid yields as well as reducing solid product fractions.³⁸⁻⁴⁰

For the cracking reactions involving a zeolite catalyst, the introduction of sterol into the feedstock resulted in a further decrease in liquid product yield. Interestingly, the proportion of solid coke produced also decreased with increasing sterol content, with significantly less coking observed in the conversion of pure cholesterol than for the RSO.

In contrast, for the reactions with the Pd/C catalyst, increasing the sterol content resulted in higher liquid yields at both reaction temperatures, perhaps indicating a greater activity for sterol conversion compared to the zeolite catalysts. The proportions of solid coke (4 – 6 %) produced from conversion of RSO over the Pd/C catalyst were lower than for the zeolites at both temperatures (350 °C and 400 °C) and did not have a strong dependence on sterol content.

The solid yields measured for Pd/C were comparable to the relative contribution of the triglyceride backbone to the overall weight of the molecule, of just over 4 % for the RSO feedstock. The higher solid yields obtained over HY and HZSM-5 zeolites decreased in proportion with increased temperature, indicating that they could include reaction intermediates. In contrast, the decomposition of cholesterol and the oil-sterol blends produced a much lower extent of coking with the exception of pure cholesterol on Pd/C. This can be explained by the fact that the decomposition of cholesterol is not hydrogen limited. Due to its multibranched structure, it is expected that extensive cracking of cholesterol would take place over the acid sites in the zeolites, leading to shorter chain alkenes. For Pd/C it is more likely that dehydrogenation of the rings will take place to form multi-ring aromatic compounds. These asphaltene type molecules, common in heavier fuel oil blends, are generally insoluble in common organic solvents such as CHCl_3 and as a consequence could potentially result in the apparent increase in solid yields. These results indicated that the lower temperature (350 °C) results in higher liquid yields. In order to investigate the prevalent mechanism for the conversion of sterol-rich feeds, the liquid samples were analysed by ^1H NMR.

3.3 Degree of catalytic conversion

1 The degree of triglyceride (TG), double bond (DB) and sterol conversion for the three feedstocks under each
2 set of reaction conditions were calculated from the NMR spectrum relative to the spectrum of the initial
3 feedstock (Figure 2). The degrees of TG and DB conversion are used to indicate the progress of the cracking
4 reaction under these conditions, while DB conversion is also indicative of the oxidative stability of the fuel
5 product (which increases with decreasing DB content). In addition, control experiments were performed to
6 compare the amount of conversion occurring

7

Authors pre-publication copy

Fig. 2 Percentage TG (black bar), DB (striped bar) and sterol (white bar) conversions over 1 hour at 350 °C (upper row) and 400 °C (lower row) for RSO (a, d), RC50 (b, e) and 100% cholesterol (c, f), in the presence of Pd/C, HY and H-ZSM5 catalysts, as well as in the absence of a catalyst (blank). Percentage conversions calculated from comparison of the integrated intensities from the NMR spectra

1
2 under these conditions in the absence of a catalyst ("blank"). The percentage conversion was determined
3 from the ratios of integrated intensities under the peaks in the NMR spectra of the feedstock and the liquid
4 fuel product (see supporting information for details). The triglyceride conversion was calculated from the
5 percentage difference in integral area corresponding to the protons on the TG backbone ($\delta = 4.0 - 4.5$ ppm)
6 normalised against the integral corresponding to aliphatic protons ($\delta = 0.5 - 3.0$) for the feedstock and the
7 product. Similarly, the DB conversion was calculated from the integral area of the alkene peak ($\delta = 5.0 - 5.5$
8 ppm) minus the area corresponding to the proton on the central carbon of the triglyceride backbone, which
9 overlaps with this region and can be calculated as one quarter of the area corresponding to the C1 and C3
10 protons of the TG backbone ($\delta = 4.0 - 4.5$), normalised against the integral corresponding to aliphatic
11 protons ($\delta = 0.5 - 3.0$). The percentage conversions of the sterol content were calculated from the
12 integrated intensities of the α -proton peaks of the hydroxyl group of the sterol ($\delta = 3.6$ ppm).

13 At the lower temperature of 350 °C (the reaction temperature giving greater liquid yields from the
14 mass balance) it is clear from the conversions in Figure 2 that a catalyst is necessary to achieve TG and DB
15 conversions above 40%. In the absence of a catalyst, low TG and DB conversion levels were observed,
16 presumably catalysed by the steel reactor.

17 The percentage conversion of both the TG and DB components at 350 °C was strongly dependent
18 on the catalyst employed. For the pure RSO just over 60% of the TG in the feedstock was converted over
19 Pd/C, compared with nearly 80% over the zeolite catalysts. However, the Pd/C catalyst appeared to be
20 more efficient at converting double bonds in the RSO at this temperature (~90% compared to <60% for the
21 zeolites). This apparent lack of conversion of double bonds over the zeolite catalysts suggests that
22 unsaturated breakdown products are being formed at the acidic sites. Typically catalytic cracking produces
23 high levels of double bonds, which subsequently oligomerize in the pores of the zeolite to produce
24 aromatic compounds, however, when hydrogen is formed in situ, the double bonds can be hydrogenated
25 yielding mainly alkanes.⁴¹

1 Interestingly, at 350 °C, for all three catalysts, the percentage TG and DB conversion was higher for
2 the RC50 mixture than for the pure RSO. As seen with the conversion of TG, the zeolite catalysts are more
3 effective at converting the cholesterol than the Pd/C. At 350 °C the DB in the 100% cholesterol feedstock
4 were fully converted by the Pd/C and ZSM-5. The HY zeolite was less efficient at converting the sterol
5 feedstock. This could be due to the smaller number of strong acidic sites in the HY zeolite, compared to the
6 H-ZSM5 catalyst.^{42,43}

7 At the higher reaction temperature of 400 °C, virtually all TG was converted irrespective of the
8 sterol in the oil or catalyst identity. Full TG conversion was observed even in the absence of a catalyst. A
9 similar trend was observed with the DB in these feedstocks. The 100% cholesterol feedstock at 400 °C was
10 converted to a similar extent to the lower temperature with HY zeolite being less effective than the other
11 catalysts screened.

12 A less consistent trend was observed regarding the cholesterol conversion over Pd/C. Whilst almost
13 full conversion was obtained at 350 °C, the conversion dropped to less than 80 % at 400 °C, even less than
14 without catalyst. A possible explanation is that the dehydrogenation of the sterol ring adjacent to the OH
15 group stabilises this group and therefore reduces conversion. It must also be considered that the OH group
16 may overlap with similar functional groups on some of the reaction products, leading to a slightly lower
17 apparent conversion.

18 While ¹H NMR gives a clear indication of the conversion of the glyceride backbone, or alcohol group
19 of the sterol, it was not possible to determine whether these products had been partially converted into
20 further oxygenated species or cracked into a useable hydrocarbon transport fuel. To further establish the
21 effectiveness of the catalysts, and the products formed, the liquid products were analysed by GC-MS.

23 3.4 Product analysis by GC-MS

24 The GC-MS traces of the liquid products from the cracking of the three feedstocks are provided in the
25 supporting information. A list of the major components recovered is also given in the supporting

information. Changing the specific catalyst used as well as the temperature of reaction (from 350 °C to 400 °C) resulted in significant differences in the product distribution.

The liquid fraction obtained from the reaction of RSO with no catalyst at 350 °C and 400 °C contained mainly organic acids with little conversion to hydrocarbon products. The conversion of cholesterol under these conditions yielded numerous fused aromatic rings. The liquid product from the conversion of pure RSO over HZSM-5 and HY at 350 °C also contained predominantly oxygenates, in particular octadecenoic acid and hexadecanoic acid, demonstrating that while the conversion of the TG is almost complete after 1 hr, the deoxygenation step occurs more slowly. The overall contribution of oxygenates was significantly reduced for the products from the RC50 50:50 oil/sterol mixture, as heavier, less volatile compounds were formed. These resembled the multi-ring structure of cholesterol, but could not be clearly identified from the GC-MS data.

When the reaction temperature was raised to 400 °C, the conversion of RSO over HY zeolite still yielded significant amounts of octadecenoic and hexadecanoic acid, whilst also producing a range of shorter chain alkanes ($C_{10} - C_{15}$), the C_{17} and C_{18} compounds undecyl-cyclohexane and dodecyl-benzene and a number of volatile naphthalenes. In comparison, the concentration of the direct deoxygenation product from octadecenoic acid, the alkene heptadecene, was low. The relatively poor deoxygenation performance of this catalyst was confirmed by oxygen elemental analysis, which showed a residual oxygen content of 7.63% (see supporting information). The addition of 50 % cholesterol led to a reduction of the relative contribution of alkanes, alkenes and acids, and the formation of additional, less volatile compounds. In contrast to HY, the product from the conversion of pure rapeseed oil over HZSM-5 at 400 °C no longer contained detectable amounts of carboxylic acids and only trace quantities of linear chain alkanes or alkenes. Instead, its main components were short-chain single-ring aromatics such as 1-ethyl-2-methylbenzene and the C_{18} aromatic dodecyl-benzene. ZSM-5 catalysts are generally found to be more selective towards aromatics than Y zeolites,¹⁴⁻¹⁶ with the differences attributed to the different accessible pore sizes of the various zeolites. Whilst the ZSM-5 pores (consisting of 10-membered rings) are large enough to

1 accommodate a single benzene molecule and thereby favour the formation of aromatics, the larger pores
2 in Y zeolites (12-ring) may allow multiple molecule condensation, resulting in the increased formation of
3 coking products.¹⁶ For the ZSM-5 catalysed reaction, the addition of sterol had a lesser impact on the
4 product distribution than for HY, with the exception of a reduction in the dodecyl-benzene yield and the
5 formation of the less volatile sterol decomposition products.

6 In contrast to the zeolites, the conversion of TG over Pd/C gave a much narrower product
7 distribution, showing a high concentration of the straight chain alkanes pentadecane and heptadecane at
8 both conversion temperatures. The reaction also produced high concentrations in the single ring C17
9 aromatics 1-methyldecylbenzene and undecylbenzene, whereas few oxygenated compounds could be
10 detected. Again these findings could be verified by oxygen elemental analysis which showed an oxygen
11 content of 6.89 % for the conversion of RO at 350 °C and only 1.40 % for the RC50 mixture at 400 °C (shown
12 in supporting information). For all the catalysts tested, higher temperatures led to improvement in the
13 selectivity towards alkanes rather than oxygenates and increased C₁₇/C₁₈ ratios.

14 Based on the GC-MS results, the reactions of RSO and 100% cholesterol over Pd/C and the two
15 zeolites appear to follow very different mechanisms. Whilst Pd/C results in high levels of deoxygenation at
16 350 °C, the higher temperature of 400 °C is required to achieve significant deoxygenation over the two
17 zeolite catalysts. As the deoxygenation products from Pd/C are predominantly C₁₅ and C₁₇ hydrocarbons, it
18 can be concluded that deoxygenation proceeds either via decarboxylation or decarbonylation. In the case
19 of the two zeolites, the presence of both C₁₇ and C₁₈ compounds suggests that deoxygenation also follows
20 the hydrodeoxygenation pathway. Whilst no water was detected in the reaction product, this may have
21 been lost during the extraction process or reacted further with the hydrocarbon products to produce CO₂
22 and additional hydrogen to drive the reaction.

23 Nevertheless the hydrodeoxygenation reaction requires significant amounts of hydrogen which,
24 under inert conditions, must be produced in situ by dehydrogenation or aromatisation of the fatty acid

1 chains. Zeolites are poor hydrogenation catalysts and the low concentrations of alkenes relative to
2 aromatics suggest that aromatisation is the preferred mechanism.

3 Using the Pd/C catalyst, the main reaction products from the conversion of rapeseed oil were
4 pentadecane and heptadecane from the decarboxylation of the C₁₆ and C₁₈ esters, and the aromatics
5 methyldecylbenzene, undecylbenzene and 1,3-dimethylbutylbenzene, presumably derived from the
6 unsaturated esters. The catalytic cracking of cholesterol at 350 °C over Pd/C yielded a range of heavier
7 aromatic compounds, such as phenyl-substituted naphthalene. The product distribution is relatively small
8 with less than 6 major components. An overabundance of these multi-ring compounds would be
9 detrimental to the low temperature properties of the resultant fuel as they form waxy solids which increase
10 the cloud point and viscosity. The heavier components seen at 25 minutes in this trace, seemingly
11 oxygenated multi-ring compounds, were not observed at 400 °C, indicating that under these conditions the
12 ring structure has been successfully cracked into a range of short chain alkanes and lighter, mono-aromatic
13 species. The addition of 50 % cholesterol to rapeseed oil resulted in the formation of many of these
14 components, such as hexaethyl benzene, but also included heavier, multi-ring compounds. In addition, it
15 led to the formation of low amounts of heneicosane (C₂₁) and tetracosane (C₂₄), but more significantly,
16 resulted in an increase in the alkane to aromatics ratio at both temperatures. This increase in the
17 proportion of alkanes suggests that cholesterol may donate hydrogen to the reaction and thereby inhibit
18 the formation of aromatics from the triglycerides. In this case hydrogen is released through the
19 aromatization of the cholesterol rings over Pd/C, as evidenced by the formation of aromatized cholesterol
20 derivatives as shown in the supporting information. It also corresponds with previous studies in the
21 literature that suggest that the aromatic content of the product is dependent on the number of double
22 bonds in the feed oil.¹⁹

23 It is clear in the conversion of sterol-rich lipids that while the zeolites gave carboxylic acid products
24 and large amounts of aromatics, cracking over Pd/C gave a more diesel-like composition of low oxygenates,

straight chain alkanes and acceptable levels of aromatics. This catalyst was therefore selected for use in the following section to convert an unrefined sterol-rich microbial oil into a hydrocarbon fuel.

3.5 Conversion of yeast oil

The yeast oil selected for this study was extracted from the oleaginous yeast *Metschnikowia pulcherrima*, and contained 18 mol% sterols. The elemental analysis of the oil showed elevated levels of both oxygen and phosphorous compared to rapeseed oil, indicating the presence of small chain oxygenates and phospholipids. A full breakdown of the elemental analysis and lipid profile is given in tables S1 & S2 in the supplementary information. Catalytic conversions of yeast oil were performed at 350 °C and 400 °C. The analysis of the product proportions and percentage conversions after 1 hr reaction over a Pd/C catalyst are presented in Figure 3a and 3b. The mass balances performed on the products of the cracking reactions showed that the conversion of the yeast oil produced a much higher proportion of solids, of up to 22 %, than the reaction of RSO and the RC50 oil/sterol mix. The thermogravimetric analysis (TGA) of the solid product formed at 350 °C indicated that the majority of the solids (~60%) was char, where roughly 40% was organic asphaltene compounds typically found in heavier fuel oils (see supporting information). At 400 °C, where 17 wt% solids were recovered, less than 1% of the solids were found to be organic molecules and the remainder of the solid product was comprised of coke. This higher level of coking is presumably the result of the presence of phospholipids, organic acids and metal contaminants as suggested by the elemental analysis of the oil. Unlike rapeseed oil, which is refined during the production process, the yeast oil was not purified following extraction. Consequently liquid yields were significantly lower. Gas yields in turn were similar at 400 °C, whereas at 350 °C a slightly higher proportion of gas was formed from the reaction of yeast oil than that of the model compounds. What is encouraging to note is that under conditions of 350 °C and 1 hr, a liquid product yield of 60% could be achieved over a Pd/C catalyst. The TG, DB and sterol conversions demonstrate that the triglycerides in the yeast oil are much more easily converted than those in RSO, as full TG conversion is achieved at 350 °C, compared to only 66 % and 88 %

a) Yeast oil mass balance

b) Yeast oil conversion

Fig. 3 a) Proportions of liquid, solid and gas-phase products from conversion of yeast oil at 350°C and 400 °C (1 hr), in the presence of a Pd/C catalyst. The product distributions from the RSO and RC50 model compounds under the same conditions are shown here for comparison; b) Percentage TG, DB and sterol conversions, calculated from NMR spectra, over 1 hour at 350°C (left) and 400 °C (right), for yeast oil in the presence of a Pd/C catalyst.

1 for pure RSO and the RC50 mixture, respectively, under the same conditions. The components of this liquid
2 fuel were consequently examined via GC-MS (Fig. 4).

3 The conversion of the yeast oils produced a higher relative proportion of pentadecane than the
4 conversion of rapeseed oil as a result of the greater proportion of C₁₆ esters in the feedstock oil. The major
5 products formed at both temperatures were pentadecane and heptadecane. The products also contained
6 significant amounts of hexadecane and octadecane, the shorter chain alkanes undecane through to
7 tetradecane, as well as the longer chain alkanes nonadecane and tetracosane. At 350 °C, approximately 3 %
8 of the hexadecanoic acid was observed, whereas full conversion was achieved at 400 °C. In contrast, no
9 residual amounts of octadecanoic acid were detected at either conversion temperature although small
10 quantities of a C₁₈ oxalic acid derivative were present. These could be a reaction product of octadecanoic
11 acid with oxalic acid impurities in the yeast oil. The reaction products contained significant amounts of the
12 alkenes hexadecene and heptadecene and as already indicated by the NMR results, the alkene content is
13 higher for the products from the reactions at 400 °C. Oxygen elemental analysis showed that a high degree
14 of deoxygenation was achieved at both temperatures, resulting in residual oxygen contents of 4.06 % at
15 350 °C and 2.49 % at 400 °C (see supporting information).

16 The products also contained a range of C₁₇ and C₁₈ single ring alkanes and aromatics, such as 1
17 methyldecylbenzene and cyclopentadecane, and the presence of undecylcyclohexane and undecylbenzene,
18 as well as dodecylcyclohexane and dodecylbenzene. This suggests that the aromatics are formed via
19 cyclohexane ring intermediates. It has previously been proposed that the formation of aromatics is strongly
20 related to the number of double bonds in the feedstock,¹⁹ so the lack of C₁₆ polyunsaturates in the yeast oil
21 could explain the absence of C₁₅ or C₁₆ chain aromatics in the GC-MS. The location of the six-membered ring
22 at the end of the of the alkyl chain suggests that the aromatics are formed by the reaction of the terminal
23 end with the double bond present in the 18:2 and 18:3 fatty acids. This also explains the high quantity of 1-
24 methyldecylbenzene which results if the bond is formed between the terminal end and the C₇ carbon, and
25 subsequently re-arranged to form the more stable six-membered ring structure.

3 **Fig. 4** GC-MS chromatograph of the conversion of yeast lipid at 350 and 400 °C with the major peaks
 4 annotated, all products are observed in both traces except compounds 5 and 9, only observed at 400

The alkane to aromatics ratios, calculated by dividing the sum of the percentage signals corresponding to alkanes by the sum of percentage signals corresponding to aromatics, were higher at 350 °C (approximately 2.8 to 3.0) than at 400 °C (approximately 1.8 to 2.0) and significantly higher than the ratios obtained from the conversion of pure rapeseed oil (approximately 0.9 (400°C) to 1.0 (300 °C)) but lower than those for the RC50 mixture (approximately 3.2 (400°C) to 3.7 (350°C)). This suggests that the sterols present in the yeast oil are acting as a potential source of hydrogen and result in increased formation of alkanes. As the amount of sterol in the yeast oil is lower than in the RC50 model mix (approximately 9 wt% c.f. 50 wt%), a lower alkane to aromatics ratio is obtained.

The presence of small quantities of octadecane and hexadecane suggest that the deoxygenation pathway is partially shifted towards hydrodeoxygenation. Again, the required hydrogen could be produced in situ by the dehydrogenation of the fatty acid chains, as shown by the presence of hexadecene in the reaction product. The relative higher concentration of hexadecane to octadecane indicates that the hydrodeoxygenation mechanism is facilitated for more saturated alkanes. In contrast, the hydrodeoxygenation mechanism is inhibited by the high number of double bonds in rapeseed oil, and therefore no C₁₈ products were formed during its conversion. As the GC-MS demonstrated that cracking of the yeast oil resulted in a complex mix of compounds including the desired aromatics, the fuel properties of the resulting fuels were then examined and compared to ULSD.

3.6 Fuel properties

The deoxygenation of yeast oil over Pd/C produced a high content of pentadecane, heptadecane and long chain single ring aromatics. Pentadecane and heptadecane both display very high cetane numbers (96 and 105 respectively) where the long chain aromatics have cetane numbers between 51-68. This is indicative of a highly promising blend for diesel fuel, which requires minimum cetane numbers of 51 in the EU.^{4, 44, 45} The fuel properties of the hydrocarbon fuels were analysed at various blend levels with mineral diesel (denoted here as USLD-1) and compared to the European diesel fuel standard EN 590. While there is no maximum cloud point requirement for temperate climatic zones, a cloud point of -10 °C or lower is required for most

European countries between 16th November and 15th March.⁴ This is achieved though further refining and additional cloud point suppressant additive packs.⁴⁶ The cloud points above freezing were determined for the fuel product using a combination of water and ice baths. Cloud points below freezing were determined using a Dairei DP-80 Cryo Porter freezer. The cloud point of the pure yeast derived fuels is reasonably high and more akin to biodiesel than mineral diesel (Fig. 5a). The blending with diesel resulted in an almost linear decrease in cloud points for all products. The cloud point of the fuels approached -10 °C at a diesel concentration of 50 %, though winter fuel additives would be needed beyond this blend level to bring the fuel into the required diesel range.

Gravimetric densities of the two yeast oil fuels were measured at 40 °C by weighing 1 mL samples of product. The acceptable fuel density range for ULSD at 15 °C is specified as 820 to 845 kg m⁻³. Both of the pure yeast fuel products have higher density than the upper limit set out in EN 590 (Fig. 5b). This in contrast to the fuels produced from hydrotreating and isomerisation, which tend to have densities below the acceptable range. This difference can be attributed to the high relative aromatic and straight chain alkane content of the yeast derived fuels.^{31,32} The addition of ULSD in turn results in a roughly linear decrease in fuel density, with both fuel products falling within the acceptable range at a 25% blend level. It is unlikely that these slightly higher densities are a major issue. Fossil diesel has a relatively constant energy density, and the gravimetric density is an important factor to regulate the maximum power output and maximum volumetric fuel consumption.³² As a result, low fuel densities may result in decreased engine performance. In contrast, the high densities seen for the deoxygenation products are expected to result in improved engine performance. The potential improvement that a high density bestows is also reflected in the energy density (Fig. 5c). In order to obtain an energy density, the energy content of the neat products was measured in a Parr 1341 Plain Oxygen Bomb Calorimeter, using the method set out in ASTM D240. As a function of mass the fuel produced at 350 °C had an energy density that is 4% higher than the ULSD-1 diesel used in this study. The fuel produced at 400 °C had the same energy density by mass as ULSD-1. However, due to the increased density the volumetric energy density was 14% higher for the fuel produced at 350 °C

Fig.5 Fuel properties of the pure and diesel blends of the two yeast derived hydrocarbon fuels produced at 350 °C and 400 °C. The cloud point is given in (a), the density in (b), the energy density (lower calorific value) in (c) and the flash point (d).

Fig. 6 The kinematic viscosity of the pure and blended yeast derived fuels

and 7% higher for the fuel produced at 400 °C. This would mean that a vehicle driven with a blend of yeast derived fuel would have a better fuel mileage than one driven with only ULSD-1.

The European Standard specifies a minimum diesel flash point of 55 °C. Flash Point testing was conducted using a Stanhope-SETA 99880-0 Flashcheck Instrument using the TAG closed cup method set out in ASTM D56. The flash points for both fuels and their diesel blend levels comfortably exceed this limit. This is not surprising, as the conversion products only contain a small percentage of volatile compounds which are able to form a combustible vapour phase.

The acceptable range of kinematic viscosity at 40 °C is 2.00 mm² s⁻¹ to 4.50 mm² s⁻¹. The kinematic viscosities of the product/diesel blends were measured at 40 °C with a calibrated Canon-Fenske Routine Viscometer No. 200 according the method set out in ASTM D445. Whilst the viscosities of the products blended with diesel were measured using a calibrated viscometer as specified in standard EN ISO 3104:1996, the viscosity was too high for the hydrocarbon fuels produced from the pure yeast oils to determine this directly. Instead, the dynamic viscosities were measured using a Bohlin rheometer and converted to kinematic viscosities by dividing the dynamic value with the density of the sample. The dynamic viscosities of the neat products were measured on a C-VOR 200 Bohling Rheometer (cone and plate: 20 mm, 1 °) at 500 rpm. The viscosities of the pure reaction products exceed the maximum value by a

large margin (Fig. 6). This is presumably due to the lack of short chain alkanes and isomerised species in the fuels, resulting in strong intermolecular attractions, as already demonstrated by their high cloud points.

The viscosities could be significantly reduced by blending with diesel, with the blends of products only slightly exceeding the upper limit of $4.50 \text{ mm}^2 \text{ s}^{-1}$ at 50:50 blends and meeting the required viscosities at 25:75 blends. Again the fuel produced at 350°C has a higher viscosity than that at 400°C , as can be seen by the larger proportion of shorter chain alkanes, and lower acid content, in the GC-MS chromatograph of the 400°C product. The high viscosity of the fuel blends precludes the use of this yeast oil in its pure form and rather it is only in a blend that it would be suitable for road transport use. Further to road use, marine diesel is another suitable application that requires aromatics for lubricity. A far higher viscosity is acceptable (up to $11 \text{ mm}^2 \text{ s}^{-1}$) is allowable for marine distillate fuels and up to $700 \text{ mm}^2 \text{ s}^{-1}$ for marine residual fuel oils.⁴⁷ The reaction products from the yeast oil could potentially be used unblended for these types of application.

4. Conclusion

Lipids derived from heterotrophic organisms have the potential to become a fundamental feedstock for future transport fuels, however, the effect of their high sterol content on their conversion had not been thoroughly investigated. In this investigation we have shown that not only can sterols be converted by catalytic cracking using relatively short reaction times, but by using a Pd/C catalyst, a fuel with a high energy density, high flash point and high proportion of high cetane number compounds as well as a reasonable level of aromaticity can be produced from an unrefined sterol-rich microbial oil. This conversion can be done without the addition of H_2 in a single step making this a potentially more sustainable fuel.

In addition, the conversion of rapeseed oil and cholesterol models were tested at catalytic cracking conditions over the three catalysts Pd/C, HY Zeolite and HZSM-5 zeolite. Full triglyceride conversion was achieved over all three catalysts, with slightly higher activities over the two zeolites. In contrast, Pd/C proved a significantly more active deoxygenation catalyst, with high levels of deoxygenation achieved at

the reaction temperature of 350 °C, compared to 400 °C for the zeolites. The addition of cholesterol to rapeseed oil resulted in a significant reduction in solid coke, especially for the two zeolites, and led to the formation of less volatile, multi-ring compounds, though a greater proportion of these heavy compounds could be successfully cracked using the higher reaction temperature of 400 °C. Cholesterol addition also led to a significant increase in the alkane to aromatics ratio obtained over Pd/C, which showed that it could potentially be used as a hydrogen donor to influence the aromatic content of the product.

The Pd/C catalyst was highly active in converting yeast lipid, containing 18 mol% sterol, derived from *M. pulcherrima*. Conversion rates were comparable to those of rapeseed oil, with a significant increase in the relative contribution of hydrodeoxygenation to the overall deoxygenation reaction. This increase was attributed to a higher degree of saturation in the yeast oil. The key fuel properties of the liquid products were tested and compared to the specifications set out in BS EN ISO 590:2009. Although none of the pure products met the requirements, especially due to their high viscosities and cloud points, at 50 % blends with diesel almost all products fell within the diesel specifications. This work has also demonstrated that blending yeast oil-derived fuel with ULSD in excess of the maximum 7% v/v biodiesel blend stipulated by the EU can result in a fuel with potentially higher performance than unblended ULSD.

Acknowledgements

The authors would like to extend their gratitude to the EPSRC for funding this work through the Doctoral Training Centre at the Centre for Sustainable Chemical Technologies, to Dr. Sarah Nash and Prof. John Price for their valued input and to Roger and Sue Whorrod for their generous donation to the University of Bath resulting in the Whorrod Research Fellowship held by the corresponding author. VPT thanks the University of Bath for funding via the award of a Prize Research Fellowship.

5. References

- [1] International Energy Agency, Key world energy statistics, Paris, 2012.
- [2] Mosnier A, Havlik P, Valin H, Baker J, Murray B, Feng S, Obersteiner M, McCarl BA, Rose SK, Schneider UA. *Energ Policy* 2013; 57: 602-14.

- 1 [3] Knothe G, Van Gerpen J, Kahl J. The Biodiesel Handbook, AOCS Press, Campaign, IL, 2005.
- 2 [4] EN 590:2009, Automotive fuels - Diesel - Requirements and test methods 2009.
- 3 [5] Tran NH, Bartlett JR, Kannangara GSK, Milev AS, Volk H, Wilson MA. Fuel 201; 89(2): 265-74.
- 4 [6] Veriansyah B, Han JY, Kim SK, Hong SA, Kim YJ, Lim JS, Shu YW, Oh SG, Kim J. Fuel 2012; 94: 578-85.
- 5 [7] Snare M, Kubickova I, Maki-Arvela P, Eranen K, Murzin DY. Ind Eng Chem Res 2006; 45: 5708-15.
- 6 [8] Deldari H, Appl Catal A Gen 2005; 293: 1-10.
- 7 [9] Abhari R, Tomlinson L, Havlik P, Jannasch N. Process for co-producing jet fuel and LPG from
8 renewable sources. USA Patent, WO2008124607, 2008.
- 9 [10] Marker TL, Kokayeff P, Abdo SF, Baldiraghi F, Sabatino L. Production of Diesel Fuel from
10 Biorenewable Feedstocks with Lower Hydrogen Consumption USA Patent, US2009193709, 2009.
- 11 [11] Myllyoja J, Aalto P, Savolainen P, Purola V, Alopaeus V, Grönqvist J. Process for the manufacture of
12 diesel range hydrocarbons USA Patent., US2011282116, 2011.
- 13 [12] Milne TA, Evans RJ, Nagle N. Biomass 1990; 21: 219-32.
- 14 [13] Weisz PB, Haag WO, Rodewald PG. Science 1979; 206: 57-8.
- 15 [14] Twaiq FA, Zabidi NAM, Bhatia S. Ind Eng Chem Res 1999; 38: 3230-3237.
- 16 [15] Chen D, Tracy NI, Crunkleton DW, Price GL. Appl Catal A Gen 2010; 384: 206-12.
- 17 [16] He Y, Barnes SE, Crunkleton DW, Price GL. Fuel 2012; 96: 469-475.
- 18 [17] Ooi YS, Zakira R, Mohamed AR, Bhatia S. Energ Fuel 2005; 19: 736-743.
- 19 [18] Ramya G, Sudhakar R, Joice JAI, Ramakrishnan R, Sivakumar T. Appl Catal A Gen 2012; 433-434:
20 170-178.
- 21 [19] Dupain X, Costa DJ, Schaverien CJ, Makkee M, Moulijn JA. Appl Catal B Environ 2007; 72: 44-61.
- 22 [20] Doronin VP, Potapenko OV, Lipin PV, Sorokina TP, Buluchevskaya LA. Petrol Chem 2012; 52: 392-
23 400.
- 24 [21] Katikaneni SPR, Adjaye JD, Idem RO, Bakhshi NN. Ind Eng Chem Res 1996; 35: 3332-3346.
- 25 [22] Botas JA, Serrano DP, García A, de Vicente J, Ramos R. Catal Today 2012; 195: 59-70.

- 1 [23] Malleswara Rao TV, Dupain X, Makkee M. Micropor Mesopor Mat 2012; 164: 148-163.
- 2 [24] Fargione J, Hill J, Tilman D, Polasky S, Hawthorne P. Science 2008; 319: 1235-38.
- 3 [25] Chisti Y. Biotechnol Adv 2007; 25: 294-306.
- 4 [26] Amaretti A, Raimondi S, Sala M, Roncaglia L, De Lucia M, Leonardi A, Rossi M. Microb Cell Fact
5 2010; 9: 73-79
- 6 [27] Larsen J, Petersen MO, Thirup L, Li HW, Iversen FK. Chem Eng Technol 2008; 31: 765-72.
- 7 [28] Angerbauer C, Siebenhofer M, Mittelbach M, Guebitz GM, Bioresource Technol 2008; 99: 3051-56.
- 8 [29] Chatzifragkou A, Makri A, Belka A, Bellou S, Mavrou M, Mastoridou M, Mystrioti P, Onjaro G,
9 Aggelis G, Papanikolaou S. Energ 2011; 36: 1097-1108.
- 10 [30] Borowitzka MA, Borowitzka LJ, Micro-Algal Biotechnology, Cambridge University Press, 1988.
- 11 [31] Pina C, Santos C, Couto JA, Hogg T. Food Microbiol 2004; 21: 439-47.
- 12 [32] Volkman JK. Appl Microbiol Biotechnol 2003; 60: 495-506.
- 13 [33] Pitt JL, Miller MW. Mycologia 1968; 60: 663-8.
- 14 [34] Rattray JBM, Schibeci A, Kidby DK. Bacteriol Rev 1975; 39: 197-231.
- 15 [35] Santomauro F, Whiffin FM, Scott RJ, Chuck CJ, Biotechnol Biofuel 2014, *in press*
- 16 [36] Bligh EG, Dyer WJ, Can J Biochem Phys 1959; 37: 911-7.
- 17 [37] Corma A, Martinez A, Pergher S, Peratello S, Perego C, Bellusi G. Appl Catal A Gen 1997; 152: 107-
18 25 [38] Huber GW, O'Connor P, Corma A. Appl Catal A Gen 2007; 329: 120-129.
- 19 [39] Kubicka D, Bejblova M, Vlk J. Top Catal 2010; 53: 168-78.
- 20 [40] Wang C, Tian Z, Wang L, Xu R, Liu Q, Qu W, Ma H, Wang B. ChemSusChem 2012; 5: 1974-83.
- 21 [41] Rao TVM, Dupain X, Makkee M. Micropor Mesopor Mat 2012; 164: 148-63.
- 22 [42] Girgis MJ, Tsao YP. Ind Eng Chem Res 1996; 35: 386-96.
- 23 [43] Park KC, Ihm SK, Appl Catal A Gen 2000; 203: 201-9.
- 24 [44] Murphy MJ, Taylor JD, McCormick RL. Compendium of Experimental Cetane Number Data, NREL,
25 Golden, Colorado, 2004.

- 1 [45] Creton B, Dartiguelongue C, de Bruin T, Toulhoat H. Energ Fuel 2010; 24: 5396-5403.
- 2 [46] Pipenger G, Hydrocarb Process 2001; 80: 79
- 3 [47] Fuel standard ISO 8217, For marine distillate and for marine residual fuels, 2010.

Authors pre-publication copy