Citation for published version:

Armstrong, AR, Kuganathan, N, Islam, MS & Bruce, PG 2011, 'Structure and lithium transport pathways in $\text{Li}_2\text{FeSiO}_4$ cathodes for lithium batteries', *Journal of the American Chemical Society*, vol. 133, no. 33, pp. 13031-13035. <https://doi.org/10.1021/ja2018543>

DOI:

[10.1021/ja2018543](https://doi.org/10.1021/ja2018543)

Publication date:

2011

Document Version

Peer reviewed version

[Link to publication](https://doi.org/10.1021/ja2018543)

This document is the Accepted Manuscript version of a Published Work that appeared in final form in *Journal of the American Chemical Society*, copyright © American Chemical Society after peer review and technical editing by the publisher.

To access the final edited and published work see <http://dx.doi.org/10.1021/ja2018543>

University of Bath

Alternative formats

If you require this document in an alternative format, please contact:
openaccess@bath.ac.uk

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Structure and Lithium Transport Pathways in $\text{Li}_2\text{FeSiO}_4$

Cathodes for Lithium Batteries

A. Robert Armstrong[†], Navaratnarajah Kuganathan[‡], M. Saiful Islam[‡] and Peter G. Bruce^{†}*

[†] School of Chemistry, University of St. Andrews, North Haugh, St. Andrews, Fife KY16 9ST, Scotland

[‡] Department of Chemistry, University of Bath, Bath, BA2 7AY, UK

p.g.bruce@st-and.ac.uk

RECEIVED DATE (to be automatically inserted after your manuscript is accepted if required according to the journal that you are submitting your paper to)

ABSTRACT. The importance of exploring new low cost and safe cathodes for larger scale lithium batteries has led to increasing interest in $\text{Li}_2\text{FeSiO}_4$. The structure of $\text{Li}_2\text{FeSiO}_4$ undergoes significant change on cycling, from the as-prepared γ_s form to an inverse β_{II} polymorph; therefore it is important to establish the structure of the cycled material. In γ_s half the LiO_4 , FeO_4 and SiO_4 tetrahedra point in opposite directions in an ordered manner and exhibit extensive edge sharing. Transformation to the inverse β_{II} polymorph on cycling involves inversion of half the SiO_4 , FeO_4 and LiO_4 tetrahedra, such that they all now point in the same direction, eliminating edge sharing between cation sites and flattening the oxygen layers. As a result of the structural changes, Li^+ transport paths and corresponding Li-Li separations in the cycled structure are quite different from the as-prepared material, as revealed here by computer modelling, and involve distinct zig-zag paths between both Li sites, and through intervening unoccupied octahedral sites that share faces with the LiO_4 tetrahedra.

Introduction

There is intense interest in investigating Li intercalation compounds that might find application as cathodes in new generations of lithium-ion batteries. In this regard, one advantage of polyoxyanion intercalation compounds compared with transition metal oxides is that the binding of oxygen in the polyoxyanions enhances stability and thus safety. Phosphate cathodes, particularly LiFePO_4 , have been extensively studied and continue to be important. The reason that silicates such as $\text{Li}_2\text{FeSiO}_4$ have attracted increasing attention recently is that iron and silicon are among the most abundant, and therefore lowest cost, elements on Earth. Developing cheap and safe cathode materials is a prime target for large scale lithium batteries in the future. Previous studies of $\text{Li}_2\text{FeSiO}_4$ have reported that more than 160 mAhg^{-1} of charge can be extracted from $\text{Li}_2\text{FeSiO}_4$, with reversible capacities of 120-140 mAhg^{-1} .^{1,2} Two other related Li intercalation hosts are known, $\text{Li}_2\text{MnSiO}_4$ and $\text{Li}_2\text{CoSiO}_4$.³ The structure of as-prepared $\text{Li}_2\text{FeSiO}_4$ was reported recently.⁴ However, it has been shown that the structure, and as a result the voltage, polarisation (and hence kinetics) of this cathode change during the first few cycles, then remain constant.^{1b} Half of all the Li, Fe and Si ions rearrange on cycling, which results in a significant change in the Li^+ diffusion pathways. Therefore, establishing the **cycled** structure of $\text{Li}_2\text{FeSiO}_4$ and its Li^+ diffusion pathways is important, in order to provide a platform on which future optimization of $\text{Li}_2\text{FeSiO}_4$ as a cathode for Li-ion batteries can be based. Here we report the crystal structure of cycled $\text{Li}_2\text{FeSiO}_4$ established using powder neutron diffraction and explore the Li^+ migration pathways using atomistic simulation techniques.

Experimental

Synthesizing phase pure $\text{Li}_2\text{FeSiO}_4$ has proved a challenge in the past; here we use the following method by Gong *et al.*, which is known to produce a single phase material.^{2d} Stoichiometric amounts of lithium acetate dihydrate (Acros), iron (II) acetate (Strem), and tetraethyl orthosilicate (Aldrich) were mixed in ethanol with 2ml acetic acid. After stirring, the suspension was transferred to a Teflon-lined autoclave and heated to 130 °C for 12 h. The resulting gel was dried under vacuum at 80 °C then mixed

with sucrose and ball-milled under acetone for 30 minutes. Following acetone evaporation, the sample was annealed under flowing nitrogen at 600 °C for 10 h. All subsequent handling was carried out in an Ar filled glove box (oxygen and water levels < 1 ppm). Powder X-ray diffraction data were collected on a Stoe STADI/P diffractometer operating in transmission mode with $\text{FeK}\alpha_1$ radiation ($\lambda = 1.936\text{\AA}$) to eliminate Fe fluorescence.

Composite electrodes ($\text{Li}_2\text{FeSiO}_4$, super S carbon and Kynar Flex 2801 -a co-polymer based on PVDF), with weight ratios 75:18:7, were constructed and incorporated into electrochemical cells with a lithium metal counter electrode and electrolyte (1 molal LiTFSI in ethylene carbonate/ diethyl carbonate 1:1). Electrochemical measurements were carried out at 50 °C using a Maccor Series 4200 battery cycler. After cycling, cells were opened in an Ar-filled glove box, the active material removed and rinsed with dry solvent to remove residual electrolyte and binder and dried. The samples were then transferred to 2mm quartz capillaries for neutron diffraction measurements. Time-of-flight powder neutron diffraction data were obtained on the Polaris instrument at ISIS at the Rutherford Appleton Laboratory. Since lithium is a neutron absorber the data for as-prepared materials were corrected for absorption. The structures were refined by the Rietveld method using the program TOPAS Academic.⁵

The atomistic modelling techniques are well-established and detailed elsewhere;⁶ the interatomic interactions are treated by effective shell-model Buckingham potentials and a three-body term for the SiO_4 units (Table S2). The transferability of this approach has proved successful in the modelling of structural, defect and ion transport properties of $\text{Li}_2\text{MnSiO}_4$,⁷ LiFePO_4 ,⁸ and a range of apatite-silicates and zeolites.^{6,9} An important feature of the methods is the treatment of full lattice relaxation of a large number of ions (> 700) around the migrating lithium ion, which is modelled by the Mott-Littleton method (embodied in the GULP code).⁶

Results and Discussion

The powder X-ray diffraction pattern of as-prepared $\text{Li}_2\text{FeSiO}_4$ is shown in Figure 1 and is in excellent agreement with previously reported data.^{1,2,4} Electrochemical cells were constructed as described above and subjected to cycling; the load curve is shown in Fig. 2. Consistent with previous reports it exhibits a

change of potential and a reduction in polarisation (separation of charge and discharge curves) during the first few cycles, indicative of a change in structure, which nevertheless stabilises after 5 cycles.^{1,2} Mössbauer measurements indicate a small amount of Fe(III) (~10%), in this sample. We have prepared materials with up to 30% Fe (III) which exhibit similar phase transition behavior as shown by the powder X-ray diffraction data in fig. S1.

Figure 1. Powder X-ray diffraction pattern for as-prepared $\text{Li}_2\text{FeSiO}_4$.

Figure 2. Variation of potential with state of charge on cycling $\text{Li}_2\text{FeSiO}_4$ at a rate of 10 mA g^{-1} (C/16) and demonstrating the change of potential and polarisation upon cycling.

Recent DFT calculations indicate that the change in structure on cycling leads to a drop in the cell voltage of ca. 0.3 V in good agreement with the observed change of potential (Fig 2), and is indicative of differences in the structure changing the site potential for lithium extraction.¹⁰

The structure of cycled $\text{Li}_2\text{FeSiO}_4$ was established using a combination of X-ray and neutron powder diffraction on material extracted from an electrochemical cell after 10 cycles. Li is a weak scatterer of X-rays but scatters neutrons relatively strongly, whereas Fe scatters both X-rays and neutrons strongly. Identifying the distribution of the Li ions in the structure is especially important as this information is used as the basis for modelling the Li^+ diffusion pathways, described later in the paper. The fitted neutron and X-ray powder diffraction patterns for $\text{Li}_2\text{FeSiO}_4$ after 10 cycles at the end of discharge are shown in Fig. 3. Li_2MSiO_4 compounds are known to exhibit complex polymorphism. Comparison of

the powder diffraction data for cycled $\text{Li}_2\text{FeSiO}_4$ with data from other Li_2MSiO_4 phases suggested structural similarity with the β_{II} polymorph of $\text{Li}_2\text{CoSiO}_4$, therefore this crystal structure was used as a starting point for refinement of the cycled $\text{Li}_2\text{FeSiO}_4$ structure.^{3d,11} An analogous model has also been suggested from DFT calculations.¹² A few small misfits were observed, which could be addressed by introducing the as-prepared structure as a minority second phase. In view of the complexity of the as-prepared structure, its atomic coordinates were fixed at the values obtained from refinement of the parent material, Table S1, whilst allowing the lattice parameters to vary. The amount of this second phase refined to 10%. An excellent fit was obtained, R_{wp} of 2.6%, Fig. 3. The particle size was extracted from the Rietveld refinement (peak widths) and a value of $\sim 30\text{nm}$ was observed, in good agreement with particle size observed in TEM (fig. S2). The final refined structure is shown in Fig. 4 with coordinates in Table 1.

Figure 3. Fitted powder diffraction patterns for $\text{Li}_2\text{FeSiO}_4$ after 10 cycles at the end of discharge. a) neutrons b) X-rays. Dots represent observed data and solid line the calculated pattern. The lower line is the difference/esd. Tick marks indicate allowed reflections. Upper tick marks correspond to as-prepared $\text{Li}_2\text{FeSiO}_4$ (included as a second phase in the refinement), lower tick marks to cycled structure.

Figure 4. Crystal structures of (a) $\text{Li}_2\text{FeSiO}_4$ at the end of discharge after cycling, space group $Pmn2_1$. All tetrahedra point in the same direction along the c -axis and are linked only by corner-sharing; SiO_4 tetrahedra are isolated from each other, sharing corners with LiO_4 and $(\text{Li/Fe})\text{O}_4$ tetrahedra. (SiO_4 tetrahedra – yellow, Li1O_4 tetrahedra – dark blue, Li2/FeO_4 tetrahedra – light blue); (b) as-prepared $\text{Li}_2\text{FeSiO}_4$, space group $P2_1/n$. In contrast to the β_{II} type structure of the cycled material, the γ_{s} structure of as-prepared $\text{Li}_2\text{FeSiO}_4$ has half the tetrahedra pointing in opposite directions in an ordered fashion

and exhibits edge sharing between pairs of $\text{LiO}_4/\text{FeO}_4$ and $\text{LiO}_4/\text{LiO}_4$ tetrahedra (SiO_4 tetrahedra – yellow, LiO_4 tetrahedra – dark blue, Li_2O_4 tetrahedra – light blue, FeO_4 tetrahedra – brown). The oxygen layers are also less buckled in the cycled material.

Table 1. Refined crystallographic parameters for $\text{Li}_2\text{FeSiO}_4$ after 10 cycles at end of discharge, space group $Pmn2_1$ Result of combined X-ray neutron refinement.

$R_e = 1.95\%$, $R_{wp} = 2.61\%$, $R_p = 2.67\%$

$a = 6.236(3) \text{ \AA}$, $b = 5.423(2) \text{ \AA}$, $c = 4.988(2) \text{ \AA}$.

Atom	Wyckoff symbol	x/a	y/b	z/c	B_{iso}
Li1	2a	0	0.147(7)	0.045(6)	0.7(-)
Si1	2a	0.5	0.175(2)	0	0.4(-)
Li2/Fe1 ^[a]	4b	0.257(2)	0.342(2)	0.417(2)	0.4(2)
O1	4b	0.277(2)	0.332(2)	0.904(3)	1.7(2)
O2	2a	0	0.109(1)	0.396(3)	0.1(1)
O3	2a	0.5	0.157(2)	0.345(3)	0.1(1)

[a] occupancy 0.49/0.51(2)

As for all Li_2MSiO_4 polymorphs, the O^{2-} ions adopt a distorted hexagonal close-packed arrangement, with half of the tetrahedral sites occupied by cations, such that face sharing is avoided. In the cycled structure, all the tetrahedra point in the same direction along the c-axis, Fig. 4, and are linked only by corner-sharing. The SiO_4 tetrahedra are isolated from each other, sharing corners with LiO_4 and $(\text{Li/Fe})\text{O}_4$ tetrahedra. In the ideal β_{II} structure, as adopted by $\text{Li}_2\text{MnSiO}_4$, the Li^+ and M^{2+} occupy different crystallographic sites. However, in cycled $\text{Li}_2\text{FeSiO}_4$ the site normally occupied by M^{2+} is occupied exclusively by Li^+ , with the remaining Li^+ sharing the conventional Li site with the Fe ions; this structure is essentially the same as that adopted by the β_{II} polymorph of $\text{Li}_2\text{CoSiO}_4$ and is somewhat analogous to the relationship between normal and inverse spinels, Table 1.¹³ Previous powder X-ray

data suggested that Li and Fe might both be distributed over two sets of sites, resulting in quite different pathways for Li migration from those reported here.^{1b} The LiO₄ sites alternate with the SiO₄ tetrahedra along the a-axis and the (Li/Fe)O₄ sites are also arranged in rows parallel to the a-axis, Fig. 4. Refinement of the Li/Fe ratio on the shared site yielded a value of 0.49:0.51(2) implying an overall composition of Li_{1.98}Fe_{1.02}SiO₄, within 1 esd of the ideal stoichiometry. This is also in good agreement with the value obtained by counting charge on cycling, Fig. 2. The load curves in Fig. 2 were collected at a low rate of 10 mAhg⁻¹ and exhibit plateaux after ~5 cycles suggesting intercalation may follow a 2-phase process. Powder X-ray diffraction data at various states-of-charge after 5 cycles indicate strong structural similarity between the charged and discharged structures; however, attempts to refine a crystal structure for the charged cycled phase were unsuccessful, due in large part to the significant peak broadening, a process that is reversible on each cycle.

Comparing the structure of as-prepared and cycled Li₂FeSiO₄ indicates that significant structural change occurs within the first few cycles; emphasizing the importance of establishing the cycled structure, Fig. 4. The structure of the former was refined using powder neutron diffraction data and gives an excellent fit (figure S3, table S1) and agreement with the structure first reported by Yamada *et al.*⁴ The space group used was $P2_1/n$, rather than the originally published $P2_1$.¹⁴ The as-prepared structure, designated γ_s by Yamada, is shown in Fig. 4. In γ_s half the Li, Fe and Si cations are in tetrahedral sites pointing along c while the other half point in the opposite direction in an ordered manner; in contrast, in the cycled structure all the Li, Fe and Si cations are in tetrahedral sites pointing in the same direction along c. . As a result of half the tetrahedra pointing in opposite directions, γ_s exhibits 2 sets of edge sharing tetrahedra; in the first set each FeO₄ shares one edge with a LiO₄ tetrahedron whereas in the second set two LiO₄ tetrahedra share a common edge, Fig 4(b); no edge sharing is observed in the cycled structure. The oxygen layers in the β_{II} type cycled structure are significantly less buckled than in γ_s and more closely approach ideal hexagonal close packing. These differences in the structure on cycling change significantly the Li⁺ diffusion pathways, something of considerable importance to the operation of the intercalation host as a cathode.

Before examining the diffusion pathways and activation energy for Li^+ ion transport, it was first necessary to consider how the Li/Fe ions that share a site might order. Diffraction data show no evidence for long range order, so any order must extend over only limited distances. Different configurations of the shared (Li,Fe) O_4 sites were considered, and included structures in which the LiO_4 and FeO_4 tetrahedra alternate regularly along the a-axis or align in parallel rows along the a-axis. The lattice energies of the various structures were then compared by performing a series of P1 geometry optimisations, allowing full relaxation of the ion positions and cell parameters. Our simulations find that the lowest energy structure, by more than 110meV, is the ordering scheme in which Li and Fe alternate regularly along the a-axis (Fig S4).

Table 2 shows a comparison of the calculated and experimental structural parameters. The calculated unit cell parameters and Li-O, Fe-O and Si-O bond lengths deviate from experiment by at most 0.09 Å, and in most cases much less (e.g. Li2-O bonds); also, the observed unit cell volume is reproduced to within 0.4%. The minor discrepancies are possibly due to the calculated configuration of shared (Li/Fe) O_4 site in the cycled structure. Nevertheless, the good reproduction of the relatively complex structure is not a trivial task, and gives us confidence that the simulation model can be used reliably in the lithium migration calculations.

Table 2. Calculated and experimental structural parameters of the cycled $\text{Li}_2\text{FeSiO}_4$ material.

Parameter	Calc	Expt
a (Å)	6.3206	6.2361
b (Å)	5.4786	5.4231
c (Å)	4.8918	4.9881
$\alpha = \beta = \gamma$ (°)	90.0	90.0
Li1– O (Å)	2.052	1.982
Li2– O (Å)	2.017	2.027
Fe – O (Å)	1.964	2.027
Si – O (Å)	1.635	1.688

The lithium diffusion paths in the cycled (β_{II}) structure of $\text{Li}_2\text{FeSiO}_4$ have not been clearly established before. Previous DFT studies¹⁵ based on earlier structural data have examined similar migration paths in the delithiated system. Our previous studies^{7,8} have shown that simulation techniques can be used to examine defects and migration mechanisms, which are often difficult to probe by experiment. For the cycled structure, we have identified two main Li migration paths illustrated in Fig. 5, with the Li-Li hop distances listed in Table 3. The first path involves corner-sharing Li1 and Li2 sites with an overall trajectory along the c-axis direction; the second path, which also involves hops between Li1 and Li2 sites but in the b direction with longer hop distances. We note that the Li^+ transport paths and Li-Li hop distances in the cycled structure are quite different from the as-prepared material, in keeping with the significant structural reorganisation; for example, our structural data for the as-prepared γ_s material (Table S1) indicates interatomic separations between adjacent Li sites of 2.64, 2.84 and 3.06 Å, with the shortest value corresponding to the edge-sharing LiO_4 tetrahedra. Hence, in contrast to the β_{II} type structure of the cycled material, the main Li migration paths in the as-prepared structure (γ_s) involves both edge- and corner-sharing LiO_4 tetrahedra with overall diffusion in the b direction and along the diagonal between the a and c axes.

Atomistic simulations were used to derive Li^+ migration energies for the paths shown in Fig 5. We also considered a range of other paths with longer Li-Li hop distances of > 4.0 Å, but these all yielded very high migration barriers (> 3.0 eV). The calculated Li^+ migration energies are listed in Table 3 and reveal two key points about the cycled structure. First, the lowest migration energy is 0.9 eV for the path in the c direction (hops A and B in Fig 5a), with a much higher barrier for the path along the b-axis. This suggests that Li transport is anisotropic and involves zig-zag paths between a corner-sharing network of Li1 and Li2 sites. The favorable Li^+ migration path involves passage through intervening vacant octahedral sites that share faces with the tetrahedral Li1 and Li2 sites. Recent DFT studies¹⁴ based on earlier structural data^[1,2a] have found Li-vacancy migration barriers of 0.9-1.0eV in the delithiated

system. It is interesting to note that the calculated migration energy is greater than the 0.6 eV reported for LiFePO_4 .^{8,16} Slower Li diffusion implies a lower rate capability for $\text{Li}_2\text{FeSiO}_4$ cathodes as Li is extracted and inserted over the composition range of the Li rich solid solution.

Figure 5. Pathways for lithium ion migration between corner-sharing Li(1) and Li(2) sites in the cycled structure of $\text{Li}_2\text{FeSiO}_4$. (a) the first path involves hops A and B in the c direction (b) the second path

involves hops C and D in the b direction (SiO_4 tetrahedra – yellow, Li(1)O_4 tetrahedra – dark blue, Li(2)O_4 tetrahedra – light blue, FeO_4 tetrahedra – brown).

Table 3. Calculated migration energies and interatomic separations for lithium-ion transport paths in the cycled structure of $\text{Li}_2\text{FeSiO}_4$.

Migration Path ^a	Li-Li Separation (calc) (Å)	E_{mig} (eV)
Hops (A) + (B)	3.03 + 3.04	0.91
Hops (C) + (D)	3.03 + 3.33	1.55

[a] Shown in Figure 5

In conclusion, the structure of cycled $\text{Li}_2\text{FeSiO}_4$ has been elucidated and the Li^+ migration pathways determined. The structure differs significantly from the as-prepared form, and, as a consequence, so to do the Li^+ diffusion pathways. In cycled $\text{Li}_2\text{FeSiO}_4$, all the Fe^{2+} and half the Li^+ share one set of tetrahedral sites (Li2/Fe) with the remaining Li^+ occupying a second set of tetrahedral sites (Li1). Li^+ transport in the cycled structure is anisotropic involving zig-zag paths between corner-sharing Li1 and Li2 sites, and through intervening vacant octahedral sites that share faces with the LiO_4 tetrahedra. The results presented here demonstrate that future work should consider how to synthesise the cycled structure directly, thus avoiding the structural changes on cycling, and how the structure may be modified to reduce the activation barrier for Li^+ diffusion thus increasing the rate capability.

ACKNOWLEDGMENT. The authors acknowledge the support of the EPSRC and the Supergen Energy Storage Consortium for funding, as well as Dr C. Eames (Bath) for useful discussions. The computations were run on the HECToR facilities via the Materials Chemistry Consortium.

Supporting Information Available.

Presented here are details of the refined structure of as-prepared $\text{Li}_2\text{FeSiO}_4$ and of the calculated structure.

This material is available free of charge via the Internet at <http://pubs.acs.org/>.

REFERENCES

- [1] a) Nyten, A.; Abouimrane, A.; Armand, M.; Gustafsson, T.; Thomas, J. O. *Electrochem. Commun.* **2005**, *7*, 156; b) Nyten, A.; Kamali, S.; Häggström, L.; Gustafsson, T.; Thomas, J. O. *J. Mater. Chem.*, **2006**, *16*, 2266.
- [2] a) Dominko, R.; Bele, M.; Gaberscek, M.; Meden, A.; Remskar, M.; Jamnik, J. *Electrochem. Commun.* **2006**, *8*, 217; b) Zaghbi, K.; Ait Salah, A.; Ravet, N.; Mauger, A.; Gendron, F.; Julien, C. M. *J. Power Sources* **2006**, *160*, 1381; c) Quoirin, G.; Taulelle, F.; Dupont, L.; Masquelier, C. *211th ECS Meeting*, **2007**, Abstract #98; d) Gong, Z. L.; Li, Y. X.; He, G. N.; Li, J.; Yang, Y. *Electrochemical and Solid-State Letters* **2008**, *11*, A60; e) Zhang, S.; Deng, C.; Yang, S.Y. *Electrochemical and Solid-State Letters* **2009**, *12*, A136; f) Boulineau, A.; Sirisopanaporn, C.; Dominko, R.; Armstrong, A. R.; Bruce, P. G.; Masquelier, C. *Dalton Trans.* **2010**, *39*, 6310; g) Sirisopanaporn, C.; Boulineau, A.; Hanzel, D.; Dominko, R.; Budic, B.; Armstrong, A. R.; Bruce, P. G.; Masquelier, C. *Inorg. Chem.*, **2010**, *49*, 7446; h) Islam M S, Dominko R, Masquelier C, Sirisopanaporn C, Armstrong A R, Bruce P G., *J. Mater. Chem.* **2011**, in press, DOI: 10.1039/C1JM10312A.
- [3] a) Gong, Z. L.; Li, Y. X.; Yang, Y. *Electrochemical and Solid-State Letters* **2006**, *9*, A542; b) Kokalj, A.; Dominko, R.; Mali, G.; Meden, A.; Gaberscek, M.; Jamnik, J. *Chem. Mater.* **2007**, *19*, 3640; c) Politaev, V.V.; Petrenko, A.A.; Nalbandyan, V.B.; Medvedev, B.S.; Shvetsova, E.S. *J. Solid State Chem.* **2007**, *180*, 1045; d) Lyness, C.; Delobel, B.; Armstrong, A. R.; Bruce, P. G. *J. Chem. Soc. Chem. Commun.* **2007**, 4890; e) Gong, Z. L.; Li, Y. X.; Yang, Y. *J. Power Sources*, **2007**, *174*, 524; f) Belharouak, I.; Abouimrane, A.; Amine, K. *J. Phys. Chem. C*, **2009**, *113*, 20733.
- [4] Nishimura, S.; Hayase, S.; Kanno, R.; Yashima, M.; Nakayama, N.; Yamada, A. *J. Amer. Chem. Soc.* **2008**, *130*, 13212.
- [5] Coelho, A. A. *J. Appl. Cryst.*, **2000**, *33*, 899.

- [6] a) Catlow, C.R.A. *Computer Modeling in Inorganic Crystallography*, Academic Press, San Diego, CA, **1997**; b) Gale, J.D.; Rohl, A.L. *Molec. Simul.*, **2003**, 29, 291
- [7] a) Kuganathan, N.; Islam, M.S. *Chem. Mater.*, **2009**, 21, 5196; b) Islam, M.S. *Phil. Trans. R. Soc. A*, **2010**, 368, 3255.
- [8] a) Islam, M.S.; Driscoll, D.J.; Fisher, C.A.J.; Slater, P.R. *Chem. Mater.*, **2005**, 17, 5085; b) Gardiner, G.R.; Islam, M.S. *Chem. Mater.*, **2010**, 22, 1242; c) Fisher C A J, Hart Prieto V M and Islam M S, *Chem. Mater.* **2008**, 20, 5907.
- [9] a) Slater, B.; Catlow, C.R.A.; Liu, Z.; Ohsuna, T.; Terasaki, O.; Camblor, M.A. *Angew. Chem. Int. Ed.*, **2002**, 41, 1235; b) Chiu, M.E.; Slater, B.; Gale, J.D. *Angew. Chem. Int. Ed.*, **2005**, 44, 1213; c) Jones, A.; Islam M.S.; Slater, P.R. *Chem.. Mater.*, **2008**, 20, 5055.
- [10] Eames C., Armstrong A.R., Bruce P.G., Islam M.S., in preparation
- [11] Armstrong, A. R.; Lyness, C.; Ménétrier, M.; Bruce, P. G. *Chem. Mater.* **2010**, 22, 1892.
- [12] Liivat, A.; Larsson, P.; Thomas, J.O. Abstract 274, IMLB 2008, Tianjin, China, **2008**.
- [13] Wells, A.F. *Structural Inorganic Chemistry*, Clarendon Press, Oxford, **1984**.
- [14] Yamada, A.; Nishimura, S. Abstract O31,, LiBD-4 , Arcachon, France, **2009**.
- [15] Liivat, A.; Thomas, J.O. *Solid State Ionics*, **2011**, in press doi:10.1016/j.ssi.2009.12.009
- [16] a) Molenda, J.; Ojczyk, W.; Świerczek, K.; Zajac, W.; Krok, F.; Dygas, J.; Liu, R.S. *Solid State Ionics* **2006**, 177, 2617; b) Amin, R.; Maier, J.; Balaya, P.; Chen, D.P.; Lin, C.T. *Solid State Ionics*, **2008**, 179, 1683.

TOC graphic