



Citation for published version:

Koketsu, T, Ma, J, Morgan, B, Body, M, Legein, C, Goddard, P, Borkiewicz, O, Strasser, P & Dambournet, D 2020, 'Exploiting Cationic Vacancies for Increased Energy Densities in Dual-Ion Batteries', *Energy Storage Materials*, vol. 25, pp. 154-163. <https://doi.org/10.1016/j.ensm.2019.10.019>

DOI:

[10.1016/j.ensm.2019.10.019](https://doi.org/10.1016/j.ensm.2019.10.019)

Publication date:

2020

Document Version

Peer reviewed version

[Link to publication](#)

Publisher Rights

CC BY-NC-ND

University of Bath

Alternative formats

If you require this document in an alternative format, please contact:
openaccess@bath.ac.uk

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Supplementary Information

Exploiting Cationic Vacancies for Increased Energy Densities in Dual-Ion Batteries

Toshinari Koketsu¹, Jiwei Ma^{2,3,4}, Benjamin J. Morgan⁵, Monique Body⁶, Christophe Legein⁶, Pooja Goddard⁷, Olaf J. Borkiewicz⁸, Peter Strasser¹, and Damien Dambournet^{2,3*}




Figure S1 (a) Cyclic voltammograms for a Pt foil working electrode (1.27 cm²) in APC with various LiCl concentrations (scan rate: 20 mV s⁻¹).




Figure S2. Discharge-charge profiles of (a) Mg/TiO₂ and (b) Mg/Ti_{0.78}□_{0.22}O_{1.12}F_{0.40}(OH)_{0.48} cells with APC + 0.2-1 M LiCl at different current densities of 20, 50, 100, 200, 300, 500 mA g⁻¹.




Figure S3. Experimental (in blue) and fitted (in dashed red) ^{19}F solid-state MAS (64 kHz) NMR spectra of the electrochemically charged electrode using hybrid electrolyte 0.2 M APC + 0.2 M LiCl. The individual resonances used for the fit are shown below (see **Table S1**).

Table S1. Isotropic chemical shifts (δ_{iso} , ppm), line widths (LW, ppm), relative intensities (I, %) and tentative and partial assignment of the NMR resonances used for the fit of the ^{19}F MAS (64 kHz) NMR spectrum of the electrochemically charged electrode using hybrid electrolyte 0.2 M APC + 0.2 M LiCl. Weighted average isotropic chemical shift value ($\langle\delta_{\text{iso}}\rangle$, ppm).

δ_{iso}	LW	I	Assignment
-3.7	27.6	5.6	F-Ti ^{IV} ₂ □, F-Ti ^{IV} Mg□, F-Ti ^{III} □ ₂ ,...
-20.3	100.9	60.5	
-53.0	28.3	4.5	...
-88.9	24.1	8.5	F-Ti ^{IV} ₃ , F-Ti ^{IV} Ti ^{III} □, F-Ti ^{IV} ₂ Mg, F-Ti ^{III} Mg,...
-159.5	11.3	0.9	F-Ti ^{IV} ₂ Ti ^{III} , F-Ti ^{III} ₂ □, F-Ti ^{IV} Ti ^{III} Mg, F-Ti ^{IV} Mg ₂ ,...
-182.4	14.0	14.4	
-199.9	14.3	5.7	F-Ti ^{IV} Ti ^{III} ₂ , F-Ti ^{III} ₂ Mg, F-Ti ^{III} Mg ₂ ,...
$\langle\delta_{\text{iso}}\rangle$		-61	




Figure S4. Experimental (in blue) and fitted (in dashed red) ^{19}F solid-state MAS (64 kHz) NMR spectra of the electrochemically discharged electrode using hybrid electrolyte 0.2 M APC + 0.2 M LiCl. The individual resonances used for the fit are shown below (see **Table S2**).

Table S2. Isotropic chemical shifts (δ_{iso} , ppm), line widths (LW, ppm), relative intensities (I, %) and tentative and partial assignment of the NMR resonances used for the fit of the ^{19}F MAS (64 kHz) NMR spectrum of the electrochemically discharged electrode using hybrid electrolyte 0.2 M APC + 0.2 M LiCl. Weighted average δ_{iso} value ($\langle\delta_{\text{iso}}\rangle$, ppm).

δ_{iso}	LW	I	Assignment
19.0	18.4	3.1	F-Ti ^{IV} ₂ □, F-Ti ^{IV} Mg□, F-Ti ^{III} □ ₂ ...
-9.4	41.7	12.9	
-50.7	51.1	28.9	...
-88.2	69.3	15.1	F-Ti ^{IV} ₃ , F-Ti ^{IV} Ti ^{III} □, F-Ti ^{IV} ₂ Mg, F-Ti ^{III} Mg□,...
-89.9	21.4	10.5	
-190.1	28.7	8.6	F-Ti ^{IV} ₂ Ti ^{III} , F-Ti ^{III} ₂ □, F-Ti ^{IV} Ti ^{III} Mg, F-Ti ^{IV} Mg ₂ ...
-203.4	10.8	21.0	F-Ti ^{IV} Ti ^{III} ₂ , F-Ti ^{III} ₂ Mg, F-Ti ^{III} Mg ₂ ...
	$\langle\delta_{\text{iso}}\rangle$	-97	




Figure S5. Experimental (in blue) and fitted (in dashed red) ^{19}F solid-state MAS (64 kHz) NMR spectra of the electrochemically charged electrode using hybrid electrolyte 0.2 M APC + 1 M LiCl. The individual resonances used for the fit are shown below (see **Table S3**).

Table S3. Isotropic chemical shifts (δ_{iso} , ppm), line widths (LW, ppm), relative intensities (I, %) and tentative and partial assignment of the NMR resonances used for the fit of the ^{19}F MAS (64 kHz) NMR spectrum of the electrochemically charged electrode using hybrid electrolyte 0.2 M APC + 1 M LiCl. Weighted average δ_{iso} value ($\langle\delta_{\text{iso}}\rangle$, ppm).

δ_{iso}	LW	I	Assignment
-10.7	66.1	23.1	F-Ti ^{IV} ₂ □, F-Ti ^{IV} Mg□, F-Ti ^{III} □ ₂ ...
-52.5	43.8	13.4	...
-71.3	155.1	19.9	F-Ti ^{IV} ₃ , F-Ti ^{IV} Ti ^{III} □, F-Ti ^{IV} ₂ Mg, F-Ti ^{III} Mg□,...
-88.5	23.1	9.0	
-182.3	17.5	27.9	F-Ti ^{IV} ₂ Ti ^{III} , F-Ti ^{III} ₂ □, F-Ti ^{IV} Ti ^{III} Mg, F-Ti ^{IV} Mg ₂ ,...
-197.9	9.4	6.8	F-Ti ^{IV} Ti ^{III} ₂ , F-Ti ^{III} ₂ Mg, F-Ti ^{III} Mg ₂ ,...
$\langle\delta_{\text{iso}}\rangle$		-96	




Figure S6. Experimental (in blue) and fitted (in dashed red) ^{19}F solid-state MAS (64 kHz) NMR spectra of the electrochemically discharged electrode using hybrid electrolyte 0.2 M APC + 1 M LiCl. The individual resonances used for the fit are shown below (see **Table S4**).

Table S4. Isotropic chemical shifts (δ_{iso} , ppm), line widths (LW, ppm), relative intensities (I, %) and tentative and partial assignment of the NMR resonances used for the fit of the ^{19}F MAS (64 kHz) NMR spectrum of the electrochemically discharged electrode using hybrid electrolyte 0.2 M APC + 1 M LiCl. Weighted average δ_{iso} value ($\langle\delta_{\text{iso}}\rangle$, ppm).

δ_{iso}	LW	I	Assignment
-85.6	58.6	7.8	F-Ti ^{IV} ₃ -F, F-Ti ^{IV} Ti ^{III} □, F-Ti ^{IV} ₂ Mg, F-Ti ^{III} Mg□, ...
-142.2	129.2	69.3	F-Ti ^{III} ₂ □, F-Ti ^{IV} ₂ Ti ^{III} , F-Ti ^{III} ₂ □, F-Ti ^{IV} Ti ^{III} Mg, F-Ti ^{IV} Mg ₂ ...
-196.3	20.3	22.9	F-Ti ^{IV} Ti ^{III} ₂ , F-Ti ^{III} ₂ Mg, F-Ti ^{III} Mg ₂ ...
$\langle\delta_{\text{iso}}\rangle$		-150	




Figure S7. Normalized ^7Li MAS (44 kHz) NMR spectra of the electrochemically discharged (EoD) and charged (EoC) electrodes using hybrid electrolyte 0.2 M APC + 0.2 M LiCl and 1 M LiCl. Expansions of the central lines are shown in the inset.




Figure S8. Experimental (in blue) and fitted (in dashed red) ${}^7\text{Li}$ solid-state MAS (44 kHz) NMR spectra of the electrochemically discharged electrode using hybrid electrolyte 0.2 M APC + 1 M LiCl. The individual resonances used for the fit are shown below (see **Table S5**). Expansions of the central lines are shown in the inset.

Table S5. Isotropic chemical shifts (δ_{iso} , ppm), line widths (LW, ppm) and relative intensities (I, %) of the NMR resonances used for the fit of the ^7Li MAS (44 kHz) NMR spectra of the electrochemically charged and discharged electrode using hybrid electrolyte 0.2 M APC + 0.2 M and 1 M LiCl. Weighted average δ_{iso} ($\langle\delta_{\text{iso}}\rangle$, ppm) and LW ($\langle\text{LW}\rangle$, ppm) values.

Sample	δ_{iso}	LW	I
EoC 0.2 M LiCl	-3.2	12.9	28.5
	-0.2	5.0	71.5
$\langle\delta_{\text{iso}}\rangle/\langle\text{LW}\rangle$	-1.1	7.2	
EoD 0.2 M LiCl	-2.5	19.0	30.6
	-0.6	7.6	69.4
$\langle\delta_{\text{iso}}\rangle/\langle\text{LW}\rangle$	-1.2	11.1	
EoC 1 M LiCl	-2.0	23.1	64.5
	-1.1	8.3	35.5
$\langle\delta_{\text{iso}}\rangle/\langle\text{LW}\rangle$	-1.7	17.9	
EoD 1 M LiCl	-1.1	22.8	52.8
	-0.5	10.6	47.2
$\langle\delta_{\text{iso}}\rangle/\langle\text{LW}\rangle$	-0.8	17.0	